

VELAN

# Cast steel valves gate, globe, and check

ASME CLASSES 150 -1500 NPS 2 - 64 (DN 50 -1600) API 600 / 623 / 594 / ASME B16.34

### **VELAN'S PROFILE**

#### **VELAN AT A GLANCE**

#### History

• Founded in 1950

#### People

• Over 1,800 employees

#### **Product line**

A world-leading range of valves across all major industrial applications

- Cast steel gate, globe, check, and ball valves
- Forged steel gate, globe, check, and ball valves
- Triple-offset butterfly valves
- Knife gate valves
- Severe service valves
- Bellows seal valves
- Steam traps

#### **Primary industries served**

- Fossil, nuclear, and cogeneration power
- Oil and gas
- Refining and petrochemicals
- Chemicals and pharmaceutical
- LNG and cryogenics
- Marine
- HVAC
- Mining
- Water and wastewater
- Pulp and paper
- Subsea

### Velan holds major applicable approvals:

- ASME Section III N and NPT for nuclear valves (since 1970)
- ISO 9001 (since 1991) and ISO 14001
- OHSAS 18001
- PED
- SIL
- GOST
- API 6A and API 6D
- TA-Luft
- Comprehensive quality programs that are compliant with the most stringent industry standards such as ISO 9001, API Q1, API 624, NCA 4000, ASME NQA-1, and 10 CFR 50 Appendix B.
- Velan has been surveyed and audited by leading organizations around the world such as Bureau Veritas, API, ASME, NUPIC, Newport News Shipbuilding, and DCMA.
- Total Process Improvement Program, including Lean Manufacturing and Six Sigma.



Velan is one of the world's leading manufacturers of cast and forged steel gate, globe, check, ball, triple-offset, knife gate, highly engineered severe service valves, and steam traps offering superior performance across all major industrial applications including: fossil, nuclear, and cogeneration power; oil and gas; refining and petrochemicals; chemicals and pharmaceutical; LNG and cryogenics; marine; HVAC; mining; water and wastewater; pulp and paper; and subsea. The company also supplies actuators and integrated control packages.

Founded in 1950, Velan has earned a reputation for product excellence and innovation by bringing to the market superior products with special emphasis on quality, safety, ease of operation, and long service life. Velan valves have an extremely broad installation base and are approved by major companies worldwide.

Velan concentrates on one business—the design, manufacture and marketing of steel valves and steam traps in a broad range of types and sizes for high performance service in a wide range of applications. The company's talented people are focused on Velan's core values of quality, reliability, innovation, and integrity and mission to be the world's leading valve brand.

#### **TABLE OF CONTENTS**

Velan's global network3
Cast steel manufacturing program 4
Total quality and process improvement systems 5
Cast steel valves - industries served 6
Fugitive emission qualification
Design of stem seals and live-loading options8
Body-bonnet design 9
API 600 Gate wedge and seats 10
API 623 Globe conical seat and API 594 Swing check disc11
Bolted bonnet gate valves 12-13
Bolted bonnet globe and stop check valves14-15
Swing check valves 16-17
Valves for special service: Hydrofluoric (HF) acid valves
Valves for special service: Cryogenic valves19
Valves for special service: Block and bleed gate valves20
Actuators and accessories 21
Bypasses, flanges, weights and Cv flow cofficients22-23
Pressure-temperature ratings 24-25
Specification of cast valve materials26
How to order cast steel gate, globe, and check valves27

### **VELAN'S GLOBAL NETWORK**

#### **Head office**



- 13 production facilities
  - 4 plants in North America
  - 4 plants in Europe
  - 5 plants in Asia

N

- 2 stocking and distribution centers
- Hundreds of distributors worldwide
- Over 60 service shops worldwide

Montreal, Canada Velan Inc.

#### **Manufacturing plants**

#### **North America**



Montreal, Canada Velan Inc., Plant 1 and 5



Montreal, Canada Velan Inc., Plant 2 and 7





 $(\mathbf{N})$ 



Mennecy, France Segault SAS



Ansan City, South Korea Velan Ltd., Plant 1



Ansan City, South Korea Velan Ltd., Plant 2



Taichung, Taiwan Velan Valvac Mfg. Co., Ltd.



Suzhou, China Velan Valve (Suzhou) Co., Ltd.



Coimbatore, India Velan Valves India Pvt. Ltd.

#### **Distribution centers**



Missouri City, TX, U.S.A. Velan Valve Corp.



Willich, Germany Velan GmbH



Granby, Canada Velan Inc., Plant 4 and 6



Williston, VT, U.S.A. Velan Valve Corp., Plant 3



Lisbon, Portugal Velan Válvulas Industriais, Lda.



Velan ABV S.r.l.

### **CAST STEEL VALVES MANUFACTURING PROGRAM**

#### CAST STEEL GATE, GLOBE, AND CHECK VALVES

be															SIZ	E (N	PS/I	DN)			•										
Valve type	ASME Class	2	<b>2</b> ½	3	4	6	8	10	12	14	16	18	20	24	26	28	30	32	34	36	38	40	42	44	46	48	50	54	56	60	64
Va		50	65	80	100	150	200	250	300	350	400	450	500	600	650	700	750	800	850	900	950	1000	1050	1100	1150	1200	1250	1350	1400	1500	1600
	150	~	~	✓	~	1	1	~	<	<	<	<	1	1	1	~	~	1	1	1	1	~	<		~	1	1	<	<	1	1
	300	<	~	✓	<	1	1	~	<	<	~	<	1	1	1	~	~	1	1	1		~	<	<	~	1		<			
GATE	600	~	1	1	1	1	1	1	~	~	~	~	1	1	1	~	1	1	1	1	1	1		~			1				
	900	1		1	1	1	1	1	~	~	~	1	1																		
	1500	1		1	1	1	1	1																							
	150	~	1	1	1	1	1	1	~	~	~	1		1																	
	300	1	1	1	1	1	1	1	1	~	1	1		1																	
GLOBE	600	1	1	1	1	1	1	1	1																						
	900	1		1	1	1	1	1																							
	1500	1		1	1																										
	150	~	1	1	1	1	1	1	~	~	1	1	1	1	1	1	1	1		1	1		~			1					
	300	1	1	1	1	1	1	1	~	~	~	1	1	1		1			1				~								
CHECK	600	1	1	1	1	1	1	1	~	~	1	1	1	1	1																
	900	1		1	1	1	1	1					1					1			1										
	1500	1		1	1	1	1	1																							

(1) For gate valves larger than NPS 42 (DN 1050), in pressure class 150 and 300, and gate valves larger than NPS 24 (DN 600) in pressure class 600 and greater, wall thickness is based on B16.34 plus additional wall thickness allowance.

Valves comply with API 600.

Valves comply with API 623.

Valves comply with API 594.

#### **GASKET MATERIALS**

VALVE TYPE	MATERIAL
Gate <sup>(1)</sup>	Class 150: corrugated steel/graphite except NPS 2–2½ (DN 50–65) spiral wound
Gale	Class 300–1500: spiral wound stainless steel and graphite
Globe	Spiral wound stainless steel and graphite
Check	Spiral wound stainless steel and graphite

#### NOTE:

CoCr alloy as used throughout this catalog refers to cobalt chrome hardfacing alloys.

#### **OPTIONAL BODY MATERIALS**

ASTM	NOMINAL	MIN. 1	EMP	MAX. 1	EMP.	VELAN
SPEC. GRADE	DESIGNATION	°F	°C	۴	°C	CODE
A216-WCB	Carbon steel	-20	-29	800	427	02
A217-WC6	1¼ Cr−½ Mo	-20	-29	1,100(1)	593	05
A217-WC9	2¼ Cr–1Mo	-20	-29	1,100(1)	593	06
A217-C5	5Cr–½ Mo	-20	-29	1,200(1)	649	04
A217-C12	9Cr–1Mo	-20	-29	1,200(1)	649	09
A352-LCB	Carbon steel	-50	-46	650	343	25
A352-LCC	Carbon steel	-50	-46	700	371	31
A352-LC2	<b>2</b> ½ Ni	-100	-73	650	343	39
A351-CF8M	18Cr–9Ni–2Mo	-425	-254	1,500(1)	816(1)	13
A351-CF3M	18Cr–9Ni–2Mo	-425	-254	850	454	14

(1) Flanged end ratings terminate at 1,000°F (538°C) for Class 150.

### **TOTAL QUALITY AND PROCESS IMPROVEMENT**

Velan's number-one priority is quality. From order entry to design engineering to the shop floor, the entire company is totally committed to offering products and services that not only meet but exceed customer expectations. All Velan valves are designed and manufactured with an emphasis on low emissions, safety, simple maintenance, ease of operation, and, above all, long and reliable service life.




#### v Total Quality Commitment v

Our aim is to offer products and services that not only meet but clearly exceed the expectations of our customers.

Through training, teamwork, and performance, our employees strive to achieve continuous improvement of all processes.

Our goal is Total Quality and On-time Delivery; our method is Total Commitment.





A.K. Velan, Founder of Velan

PED

TA-Luft

API

SIL

#### **Total Process Improvement**

While Velan has always made quality a priority, in 1990 the company adopted a formal Total Quality Management Program, aimed at improving production processes and was awarded ISO 9001 status the following year.

Today, Velan's **Total Process Improvement Program** brings together a group of industry best practices, including **Lean Manufacturing** and **Six-Sigma**, with the goal of creating a more balanced and efficient production system.

#### **CERTIFICATIONS AND APPROVALS**

- ASME N/NPT (since 1970)
- ISO 9001 (since 1991)
- ISO 14001
- OHSAS 18001
- TR-010 and TR-032

6 Systems ensure the final quality goals

#### 1. Design

All valves are designed to comply with the requirements of ASME B16.34, the API standards, and special customer requirements, as applicable.

#### 2. Quality assurance

Every step from procurement through production, welding, assembly, testing, and packaging is in accordance with written quality programs and procedures-an ASME Section III manual for code valve production and an ISO 9001 QA manual for all other production. Velan's four North American plants are certified to IS0 9001 and five plants have ASME N type certificates of authorization. Velan has been fully approved to supply CE marked valves in accordance with the PED (European Pressure Equipment Directive). Orders are reviewed by the Engineering and QA departments and all special customer requirements are incorporated into QCI (Quality Control Instructions) issued for each project. The QA Department also maintains calibration and gauge-control systems, and trains and qualifies skilled welders and NDT inspectors.

#### 3. Quality control

The QC Department is responsible for all aspects of quality, from receiving of material to control of machining processes, welding, nondestructive examination, assembly, pressure testing, cleaning, painting, and packaging. When required, a permanent record of all completed quality goals is prepared and sent to customers in the form of a "Valve Data Package."

#### 4. Pressure testing

Each valve is pressure tested in accordance with ASME B16.34, API 598, or special customer requirements as applicable. In all plants test status is integrated into production control/inventory management software.

#### 5. Improvement teams

Continuous improvement teams at point of manufacturing ensure quality at source, process control, higher quality workmanship, and operator ownership.

#### 6. Qualification testing

A key to reliability is the performance of functional qualification tests. These tests are performed on all valves to determine reliability and service life.

#### **Certifications and approvals**

Velan holds major applicable approvals, including ASME N/NPT, ISO 9001, ISO 14001, OHSAS 18001, PED, API, SIL, TA-Luft, etc. Velan designs and manufactures valves in accordance with ASME B16.34 and other recognized International standards such as API and ASME Section III; we implement comprehensive quality programs that are compliant with the most stringent industry standards such as ISO 9001, API Q1, NCA 4000, ASME NQA-1, and 10 CFR 50 Appendix B.

Velan has been surveyed and audited by leading organizations around the world such as Bureau Veritas, API, ASME, NUPIC, Newport News Shipbuilding, and DCMA.


### **VELAN CAST STEEL VALVES**

#### Tight shutoff and low emissions for the process and power industries

Velan's comprehensive line of cast steel gate, globe, and check valves features leading-edge design, engineering, and manufacturing technology. Our valves meet the most stringent national and international standards for fugitive emissions including API 624 and ISO 15848-1.

Our gate, globe, and check valves are widely used in many industries including:

- Process industries: oil, chemical, petrochemical, refining, pulp and paper, pharmaceutical, mining, food processing, and water treatment.
- **Power industries:** nuclear, fossil fuel (coal and gas), and renewable and district heating.
- **Upstream and midstream industries:** Offshore production platforms, LNG liquefaction and regasification terminals, tankers carriers and tank farms, and ship-building.



Cast steel valve installation at an oil refinery.



Carbon steel gate valve, ASME Class 600 used for boiler feed water installation at a hydrogen plant in Texas.



A geothermal power plant valve installation for sour gas service.



Gate valves in service for a boiler feed installation.

### **FUGITIVE EMISSION QUALIFICATION**

#### The importance of fugitive emission (FE) testing and qualification

In a typical petroleum plant, 60% of fugitive emissions are from valves. Therefore it is extremely important to reduce valve emissions to the greatest degree possible. The four widely recognized standards regarding valve fugitive emissions for gate and globe cast steel valves are API 622, API 624, ISO 15848-1 and ISO 15848-2.

#### API 622

The primary intention of API 622 is to qualify performance of graphite packing sets, from the perspective of FE, stem corrosion and packing material properties. These tests are typically performed in test fixtures.

#### **API 624**

The primary intention of API 624 is to type test multiturn valve designs equipped with graphite packing to a maximum of 100 ppm FE using Methane gas and EPA method 21.

#### API standard 624 FE test in a valve

We certify that Velan API 600 gate and API 623 globe valves have been qualified to API Standard 624 *Type Testing of Rising Stem Valves Equipped with Flexible Graphite Packing for Fugitive Emissions.* 

Certified test reports and performance results are available upon request.

Note that valves greater than NPS 24 (DN 600 and API 594 check valves do not fall under the scope of the API 624 standard so the valves are not marked API 624 but utilize the same low fugitive emission technology.

All API 624 qualified valves use API 622 qualified packing sets.



Velan's API 624 research and development test lab. Velan's R&D department is fully equipped for testing API 624, API 622, ISO 15848-1, and ISO 15848-2 as well.

#### ISO 15848-1

The primary intention of ISO 15848-1 is to type test the valve design for FE using either Helium or Methane gas. This specification provides numerous testing parameters and FE performance options, which need to be specified or agreed between valve buyer and manufacturer.

#### ISO 15848-2

The primary intention of ISO 15848-2 is to specify production testing requirements for FE performance of newly produced valves, in production and from a QA/QC perspective.

### ISO 15848-1 type test and ISO 15848-2 production tests

In addition to API 624 qualification, Velan has also dual qualified its API 600 gate and API 623 globe valves to ISO 15848-1 class A with methane gas.


Contact us for specific solutions regarding ISO 15848-1 with Helium gas as well as ISO 15848-2 production test requirements.




All our FE qualification reports are either third party witnessed or performed at an independent laboratory. Velan also provides a low fugitive emissions certificate for Velan API 600 gate, API 623 globe, and API 594 check valves.

### **DESIGN OF STEM SEALS**

## Velan offers standard cast steel bolted bonnet gate and globe valves that are qualification tested for compliance with EPA fugitive emissions regulations, API 622, API 624, as well as ISO 15848-1





The Velan stem seal evolved from these test findings:

- Ensures leakage of less than 100 ppm as demonstrated through extensive laboratory testing.
- Velan's low emission valve technology meets latest standards requirements, with a design optimized for extended service life:
  - a. Lower compression packing design reduces friction and allows more room to re-torque in the field;
  - Rugged packing gland to withstand continued field maintenance and provides lower total cost of ownership;
  - c. Optimized packing ring construction for excellent sealing and a corrosion inhibitor which demonstrated no corrosion indication based on API 622 tests.
- Tight clearances and tolerances between vital parts.
- Precision stem and packing chambers.
   Straightness, roundness, and fine finish of the stem and packing chamber wall are essential.
- Short and narrow packing chambers improve sealing.
- Stem and packing chamber walls. Superior burnished surface finish for the stem and packing chamber.
- Hardened stem for longer life.

#### **Live-loading options**

**Velan has extensive experience in valve live-loading.** The original live-loading concept was developed by Velan in 1972 in a research project for AECL to eliminate leakage in nuclear service. Velan has been supplying live-loaded valves for Nuclear and nonnuclear service for over 40 years.

#### Live-loading.

Two sets of belleville springs extends the low emission service life especially in service with large pressure/ temperature transients or frequent cycling.

#### • Leak-off.

For critical service, a lantern ring and double packing can be provided with a leak-off connection. The leak-off is provided to allow collection of leakage from the lower packing set.

### **CAST STEEL VALVE BODY-BONNET DESIGN**


#### **Gasket design for gate valves** with oval flanges

Standard corrugated steel gaskets without graphite as specified in API 600 were found to be an unacceptable choice for low emission service, even under ideal laboratory test conditions, and regardless of the flange finish and gasket load.

After testing several alternative gaskets, we selected the best performing gasket in our tests a corrugated steel gasket with graphite-filled channels as illustrated below.



#### **Oval body-bonnet gasket**




#### **Design features**

- We certify that this gasket has been qualified to meet the requirements of API 624.
- Requires no retorquing after long cycling.
- Effective under wide fluctuations of temperature and pressure.
- Insensitive to flange finish.
- Steel walls of graphite channels provide additional protection from oxidation, corrosion, and blow-out.
- Seal offers the advantage of flexible graphite (0 –14pH, -328°F to +2,000°F).
- Low stress sealing capability.
- Modern torquing methods.

Gate	Class 150	NPS 2–64 (DN 50–600)
------	-----------	----------------------

## Gasket design for gate valves with round flanges





#### Round body-bonnet gasket

#### **Design features**

- **Full enclosure** to allow gasket to retain positive radial support during loading.
- We certify that this gasket has been qualified to meet the requirements of API 624.
- Accurate control of compression through close tolerance of gasket groove and allowance for radial expansion.
- No radial machine marks.
- Close tolerance (± 0.005" or 0.13 mm) for gasket thickness.
- Seal offers the advantage of flexible graphite (0 –14pH, -328°F to +2,000°F).
- Modern torquing methods.

Gate	Class 150 Class 300–1500	NPS 2–2½ (DN 50–65) NPS 2–36 (DN 50–900)
Globe	Class 150–600	NPS 2–16 (DN 50–400)
Check	Class 150-1500	NPS 2–36 (DN 50–900)

(1) Other materials are available.

### **VELAN API 600 GATE VALVES**


#### FLEXIBLE WEDGE VERSUS SOLID WEDGE



#### Flexible round wedge pioneered by Velan

- Universal use for temperatures up to 1,000°F (538°C).
- Flexibility compensates for seat face distortion.
- Compensates for deformation of body due to pipe stresses.
- Long cycle life.
- Ideal for processes with large temperature fluctuations.
- Assures valve tightness on both seats over wide range of pressures.
- Stem-to-wedge connection is inside the seating faces supporting the wedge ears during opening. More robust with less mass.





### Velan standard ground and lapped seal welded seat rings faced with CoCr alloy

- Pioneered by Velan and considered state-of-the-art technology.
- Welded-in leakproof. Weld quality 100% tested.
- CoCr alloy seating faces for long service life.
- Seat surface ground and lapped after weld-in.
- Standardized use for steam up to 1,000°F (538°C), oil and gas.
- CoCr alloy face will wear less than the 13Cr wedge, which can easily be repaired or replaced.



#### Classical solid wedge on competitive designs

- Wedge may cause severe jamming at temperatures over 200°F (93°C).
- Suitable for small valves NPS <sup>1</sup>/<sub>2</sub> –2 (DN 15–50).
- Wedge will stick when valve is closed hot and allowed to cool.
- No compensation for deformation of body due to pressure-temperature or pipe stresses.
- Difficult to make valve tight on both seats due to seat face distortion.

#### API 600 GATE VALVE SEAT TIGHTNESS

- Welded-in CoCr alloy faced seats and a flexible wedge in 13Cr, SS 316, Monel, or hardfaced with CoCr alloy.
- Seating faces ground and lapped to 2 RMS.

### Factory acceptance standard for gate valve seat leakage

e:	ze		Multiplier K										
5	ze	Velan	API 598 – 2009										
NPS	DN	standard	Low-pressure test	High-pressure test									
≤ <b>2</b>	≤ 50	0	0	0									
2½–12	65–300	0	4	2									
14 ≥	350 ≥	2	4	2									

Allowable leakage = (K) x (NPS)

Bubbles/min. for low-pressure test Drops/min. for high-pressure test


### **VELAN API 623 GLOBE VALVES CONICAL SEATS**


- Line contact seal.
- Non-rotating stem, torque arm and a body guided disc – easily adaptable to actuation and easier to seal.

-

- Seat has good elasticity.
- Low closing torques.
- Ideal for high pressure-temperature.

### **VELAN API 594 SWING CHECK VALVES**





#### Swing check disc assembly detail

- Cage unit design with no penetration of body prevents:
  - a) No possibility of leakage with gasketed or packed hinge pin.
  - b) No possibility of pin ejection.


- All parts are accessible from the top for easy servicing.
- Welded-in seat faced with CoCr alloy.
- Non-rotating disc.
- Ground and lapped seating surfaces.

\* CoCr alloy as used throughout this catalog refers to cobalt chrome hardfacing alloys.

### **VELAN CAST STEEL API 600 GATE VALVES**

#### **BOLTED BONNET CAST CARBON, STAINLESS OR ALLOY STEEL**

NPS 2-64 (DN 50-1600), ASME CLASSES: 150-1500



ASME CLASS	FIGURE NUMBER
150	0064C
300	1064C
600	2064C
900	7064C
1500	3064C

#### STANDARD MATERIALS

PART	MATERIALS										
Body <sup>(1)</sup>	WCB	WC6	WC9	CF8M							
Bonnet <sup>(1)</sup>	WCB	WC6	WC9	CF8M							
Stem(1)(3)		SS 410		SS 316							
Wedge <sup>(1)</sup>	CA 15 or 13Cr faced WCB	CA 15 or 13Cr faced WC6	CA 15 or 13Cr faced WC9	CF8M							
Seat <sup>(1)(2)</sup>	CoCr alloy faced carbon steel	CoCr alloy faced F11	CoCr alloy faced F22	CoCr alloy faced F316							
Packing flange		Stainless steel									
Gland bushing		Stainless steel									
Packing ring <sup>(1)</sup>		Graphite									
Gland stud		Gr. B or B7(4)									
Gland nut		Gr. 8M									
Body/bonnet nut	Gr. 2H	Gr. 8M									
Body/bonnet stud	B7		B16	B8M or 630							
Back seat <sup>(1)(3)</sup>		SS 410		SS 316							
Gasket <sup>(1)</sup>	Class 150: corrugated steel/graphite Class 300–1500: spiral wound stainless steel/graphite										
Key		Carbon s	steel								
Yoke bushing		Carbon steel		Stainless steel							
Bearing		Stee									
Handwheel nut		Malleable iro	n or steel								
Handwheel <sup>(1)</sup>		Malleable iron or	ductile iron								
Grease fitting		Stee	l								
Groove pin		Carbon steel		Stainless steel							
Bushing		Carbon steel		Stainless steel							
Washer		Carbon steel		Stainless steel							
Name plate		Stainless	steel								
Identification tag		Stainless	steel								
Rivet		Stainless	steel								
Stem nut		A 439 Austenitic duc	tile iron Gr. D-2C								

(1) Other materials available. (2) Hardfaced. (3) Hardened.

(4) For eye bolts Gr.B, for studs B7 is used.

(5) For eye bolts F316, for studs B8M or 630 is used.

#### **Design features**

- Universal trim. 13Cr stem, wedge in CA 15 or 13Cr faced, and CoCr alloy faced seat API Trim 8 suitable for applications up to 850°F (454°C).
- **Seat face** CoCr alloy hardfaced, ground, and lapped to a mirror finish.
- Flexible wedge with low center stem-wedge contact, in solid CA15 (13Cr) or hardfaced with 13Cr, SS 316, Monel or CoCr alloy. Wedge is ground and lapped to a mirror finish and tightly guided to prevent dragging and seat damage. A CoCr alloy hardfaced CF8M wedge is also available.
- Non-rotating stem with precision ACME threads and burnished finish. Double ACME for faster operation.
- Body and bonnet joint accurately machined. Gasket materials on page 4, details on page 9.

- **Body and bonnet** castings are precision machined. One-piece bonnet<sup>(1)</sup> for better alignment and fewer parts.
- Gland has two-piece construction for easy alignment.
- Flanges: ASME Classes 150–300: <sup>1</sup>/<sub>16</sub>" raised face. ASME Classes 600–1500: <sup>1</sup>/<sub>4</sub>" raised face. Finish 125–250 AARH for all valves.
- Rotating stem nut is Austenitic ductile iron Gr. D-2C renewable in line (as shown). Thrust bearings are supplied as follows:

ASME Classes 150–300: NPS 10–12 (DN 250–300), 1 bearing (top) NPS 16 (DN 400) and up, 2 bearings

ASME Classes 600-1500: NPS 6 (DN 150) and up.

(1) One-piece bonnet for Class 150 up to NPS 16 (DN 400) and Class 1500 up to NPS 6 (DN 150) only.

#### **DESIGN SPECIFICATIONS**

ITEM	APPLICABLE SPECIFICATION
Wall thickness and general design $\leq$ NPS 42 in Pressure Class 150 and 300 and $\leq$ NPS 24 in Pressure Class 600 and greater.	API 600
Wall thickness and general design > NPS 42 in Pressure Class 150 and 300 and > NPS 24 in Pressure Class 600 and greater.	ASME B16.34 plus additional allowance
Pressure-temperature rating	ASME B16.34
Face-to-face dimensions	ASME B16.10 for butt weld and flanged valves
Flange design	ASME B16.5
Butt welding design	ASME B16.25
Materials	ASTM

For information on BELLOWS SEAL VALVES see VEL-BS catalog.

#### GATE VALVE DIMENSIONS

SIZE	E ASME CLASS 150							ASME	CLASS	300		ASME CLASS 600						ASME	CLASS	S 900		ASME CLASS 1500				
NPS DN		4	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	Α	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	A	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	A	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	Α	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	E
2	<b>BW</b> 8.50	<b>FLG</b> 7.00	15.63	20.38	2.00	8	8.50	15.63	20.38	2.00	8	11.50	15.66	20.51	2.00	8		21.25	29.00	1.88	10		21.25	20 00	1.88	
50	216	178	397	518	51	203	216	397	518	51	203	292	398	521	51	203	368	540	737	48	254	368	540	737	48	254
2½ 65	9.50 241	7.50 191	16.88 429	22.14 562	2.50 64	8 203	9.50 241	16.94 430	22.20 564	2.50 64	8 203	13.00 330	18.59 472	24.19 614	2.50 64	10 254	_	-	-	-	-	-	-	-	-	-
3 80	11.13 282	8.00 203	18.56 471	24.26 616	3.00 76	10 254	11.13 283	20.22 514	26.38 670	3.00 76	10 254	14.00 356	21.63 549	27.78 706	3.00 76	10 254	381	25.75 654	34.50 876	2.88 73	14 356	18.50 470	25.75 654	876	2.75 70	14 356
4 100	12.00 305	9.00 229	22.25 565	28.32 719	4.00 102	10 254	12.00 305	23.90 607	30.95 786	4.00 102	10 254	17.00 432	25.75 654	32.76 832	4.00 102	14 356	18.00 457	28.75 730	37.50 953	3.88 99	18 457	21.50 546	28.75 730	37.50 953	3.63 92	18 457
6 150	15.88 403	10.50 267	31.19 792	38.00 965	6.00 152	14 356	15.87 403	32.31 821	40.38 1026	6.00 152	14 356	22.00 559	36.28 922	44.18 1122	6.00 152	20 508	24.00 610	39.00 991	49.00 1245	5.75 146	20 508	27.75 705	39.00 991	49.00 1245	5.38 137	(2)
8 200	16.50 419	11.50 292	38.19 970	46.13 1172	8.00 203	18 457	16.50 419	40.94 1040	50.16 1274	8.00 203	18 457	26.00 660	43.72 1110	53.25 1353	7.88 200	24 610	29.00 737	51.75 1315	62.75 1594	7.50 191	(2)	32.75 832	45.25 1149	60.00 1524	7.00 178	(2)
10 250	18.00 457	13.00 330	47.16 1198	56.28 1430	10.00 254	20 508	18.00 457	49.19 1249	59.87 1521	10.00 254	20 508	31.00 787	49.06 1246	59.87 1521	9.75 248	30 762	33.00 838	57.75 1467	67.25 1708	9.38 238	(2)	39.00 991	57.75 1467	71.00 1803	8.75 222	(2)
12 300	19.75 502		55.91 1420	66.75 1695	12.00 305	20 508	19.75 502	59.00 1499	70.61 1763	12.00 305		33.00 838	61.13 1553	72.74 1848	11.75 298	30 762		66.57 1691	83.00 2108	11.13 283	(2)	44.50 1130		92.00 2337	10.38 264	(2)
14 350			61.50 1562	75.50 1918	13.25 337	24 610	30.00 762	61.38 1559	77.75 1975	13.25 337		35.00 889	72.50 1842	83.50 2121	12.88 327	(2)		73.88 1877	90.00 2286	12.25 311	(2)	-	-	-	_	-
16 400		16.00 406	68.75 1746	85.00 2159	15.25 387	24 610	33.00 838	68.75 1746	85.50 2172	15.25 387		39.00 991	82.25 2089	91.00 2311	14.75 375	(2)	44.50 1130		100.00 2540	14.00 356	(2)	_	_	_	_	-
18	26.00 660	17.00	73.25	90.00 2286	17.25 438	24 610	36.00 914	77.88	94.00 2388	17.00 432	(2)	43.00 1092	87.06 2211	116.00 2946	16.50 419	(2)	-	2040	2340	0.00						$\left  - \right $
20	28.00	432	83.00	100.00	19.25	30	39.00	86.50	100.00	19.00		47.00	103.00	123.00	18.25	(2)	_	A	SME C	lass	es 9(	00-25	500 Fe	oraea	l gate	e
500 24	711 32.00		2108 97.00	2540 115.00		762 30	991 45.00	2197 101.25	2540 125.00	483 23.00		1194 55.00	2616 115.00	3124 132.00	464 22.00		_					so av		•	gut	
600 26	813 34.00			2921 125.00		762	1143 49.00	2572 114.50	3175 125.00			1397 57.00	2921 103.86	3353 125.00	559 21.38	(2)			See			and			'e	
650 28	864 36.00			3175 130.00	635 27.00	(2)	1245 53.00	2908 118.63	3175 130.00			1448 61.00	2638 108.25	3175 135.00	543 23.00	(2)	-							-		
700	914 36.00	610 24.00	3013 124.13	3302 140.00	686 29.25	(2)	1346 55.00	3013 124.13	3302 145.00	686 29.25	(2)	1549 65.00	2750 122.50	3429 150.00	584 24.75	(2)	-			←		E		•		
750	914	610	3153	3556 150.00	743	(2)	1397 60.00	3153 129.63	3683 150.00	743	(2)	1651	3112 145.06	3810 170.00	629 29.25	(2)						Π				
800 34	965 40.00	660	3293	3810	781	(2)	1524 64.00	3293	3810	781	(2)	1778	3684 138.00	4318	743	(2)										
850	1000	700	3632	4140	832	(2)	1626 68.00	3750	4267 185.00	832 35.25	(2)	1930 68.00	3505 145.13	4750	787	(2)					f	40				
900	1016	711	3726	4318	895	(2)	1727	3754	4699	895	(2)	1727	3686	4318	737	(2)					1					
38 950	41.00	29.00 736	155.91 3960	175.00	927	(2)	-	-	-	-	-	86.00 2184	121.00 3073	162.00 4115	34.50 876	(2)	_				ł	11	5	В,	С	
40 1000	1067	762	158.66 4030	4775	978	(2)	76.00 1930	4242	190.00 4826	978	(2)	90.00 2286	175.00 4445	198.00 5030	36.38 924	(2)	-			Û	4		Ĥ			
42 1050	44.00 1118	31.00 787	166.50 4229	195.00 4953	40.25 1022	(2)	76.00 1930	167.00 4242	190.00 4826	38.50 978	(2)	-	-	-	-	-	-		1		Q,	IV	18			
44 1100	-	-	-	-	-	-	80.00 2032	186.75 4743	286.00 7264	42.25 1073	(2)	98.00 2490	185.00 4700	211.00 5360	40.50 1028	(2)	-		<b>_</b>	_	4	Ŀ.				
	43.00 1092			225.00 5715		(2)	80.00 2032	189.47 4813	193.92 4926	42.25 1073	(2)								D	_	-	).(.		_*		
48 1200	-	36.00	189.81	225.00 5715	46.00	(2)	88.00 2235	201.68 5123		46.00 1168		-	-	-	-	-	-				1	0.				
50 1250	-	38.00	204.06	231.00 5867	47.25	(2)	-	-	-	-	-	110.00 2794	214.00 5435	230.00 5842	46.00 1168	(2)	-			-		<b>A</b> —				
54 1350	-	40.00	216.56	248.00 6299	51.50		90.00 2286	232.03 5894	250 6350	51.75 1314	(2)	-	-	-	-	-	-	BW = Butt weld								
56 1400	-	41.00	228.00	258.25	53.69		-	-	-	-	-	-	-	-	-	-	-		FL	= F	lang	ged				
60	-	1041 42.00	238.80	6458 275.00	57.50	(2)	-	-	-	-	-	-	_	-	_	-	-		$\mathbf{B} = 0$ $\mathbf{C} = 1$							
1500 64 1600		44.00	259.5	6985 300.00	61.25		_	_	-	_	-	_	_	_	_	-	-		<b>U</b> = 1	1311	iaiil	iiiiy	neigi	i i t		
1600		1118	6591	7620	1556	(2)																				


(1) Height does not include actuator. (2) Gear actuator.

(3) Butt weld and flanged valves have the same end-to-end dimensions for class 300 and up.

### **VELAN CAST STEEL API 623 GLOBE & STOP CHECK VALVES**

#### **BOLTED BONNET CAST CARBON, STAINLESS OR ALLOY STEEL**

NPS 2-24 (DN 50-600), ASME CLASSES: 150-1500



### All sizes and pressure classes have conical seats.

For Bellows seal valves see our on-line catalog (VEL-BS) at www.velan.com

#### **Design features**

- Non-rotating stem with precision ACME threads and burnished finish. Valve suitable for horizontal installation.
- Universal trim. 13Cr stem, 13Cr faced disc, and CoCr alloy faced seats

API Trim 8 suitable for service up to 850°F (454°C).

• Seat face CoCr alloy hardfaced, ground, and lapped to a mirror finish. Conical seat machined to fine surface finish.

#### Tapered disc.

Body guided disc accurately mates the hardfaced surface of the disc with the surface of the seat, hardfaced with 13Cr, CoCr alloy, SS 316, or Monel, ground and lapped with seat.

Disc in SS 316 hardfaced with CoCr alloy also available.

NPS 2–6 (DN 50–150) valves may have solid CA15 (13Cr) discs.

#### Body and bonnet.

Castings are precision machined. One-piece bonnet for better alignment, fewer parts.

- Stuffing box machined to fine surface finish.
- Body and bonnet joint accurately machined to fine surface finish. Fully enclosed gasket. Gasket materials on page 4. Details on page 9.
- Gland has two-piece construction for easy alignment.
- Rotating stem nut. Austenitic ductile iron Gr. D-2C, renewable in-line.
- **Torque arm** reduces wear on packing rings and enables better sealing and reduces torque.
- Impactor handwheels.

Globe and stop check valves require higher closing torques than gate valves with the same seat diameter and pressure class. The most economical mechanism for tight shutoff is the impactor handwheel. Two lugs cast under the wheel strike simultaneous blows and give 3–10 times the closing force of standard handwheels. Impactor handwheels are supplied at manufacturer's option unless specified by customer (see page 21).

#### Flanges:

ASME Classes 150–300:  $\frac{1}{16}$ " raised face. ASME Classes 600–1500:  $\frac{1}{4}$ " raised face. Finish 125–250 AARH for all valves.

#### **STANDARD MATERIALS**

PART		MATE	RIALS							
Body <sup>(1)</sup>	WCB	WC6	WC9	CF8M						
Bonnet <sup>(1)</sup>	WCB	WC6	WC9	CF8M						
Seat <sup>(1)(2)</sup>	CoCr alloy faced carbon steel	CoCr alloy faced F11	CoCr alloy faced F22	CoCr alloy faced F316						
Disc	CA 15 or faced A105	CA 15 or 13Cr faced F11	CA 15 or 13Cr faced F22	CF8M or F316						
Disc nut	Carbon steel		SS 304 or 316							
Stem <sup>(1)(3)</sup>		SS 410		SS 316						
Backseat <sup>(1)(3)</sup>		SS 410		SS 316						
Packing ring <sup>(1)</sup>		Graphite								
Gland stud		Gr. B or B7 <sup>(4)</sup>		F316, B8M or 630 <sup>(5)</sup>						
Gland nut		Gr. 2H		Gr. 8M						
Packing flange		Carbon steel								
Gland bushing		Carbon steel		SS						
Bonnet stud	B7	E	316	B8M or 630						
Bonnet nut	Gr. 2H	e e	ir. 4	Gr. 8M						
Hinge pin		Steel		SS						
Gasket <sup>(1)</sup>	Spira	wound stainle	ss steel/graphite	;						
Torque arm		Carbon s	steel							
Yoke bushing		Stainless steel								
Stem nut	A 439	Austenitic ducti	le iron Gr. D-2C							
Handwheel nut		Malleable iron or steel								
Handwheel <sup>(1)</sup>	Ma	alleable iron or	Ductile iron							

(1) Other materials available.

(2) Hardfaced.

(3) Hardened.

(4) For eye bolts Gr.B, for studs B7 is used. (5) For eye bolts F316, for studs B8M or 630 is used.

**GLOBE VALVE DIMENSIONS** 

#### **DESIGN SPECIFICATIONS**

ITEM	APPLICABLE SPECIFICATION
General design	API 623
Wall thickness	API 623
Pressure-temperature rating	ASME B16.34
Face-to-face dimensions for butt weld and flanged valves	ASME B16.10
Flange design	ASME B16.5
Butt welding design	ASME B16.25
Materials	ASTM

		FIGURE NUMBERS	
ASME CLASS	GLOBE	STOP CHECK	NEEDLE
150	0074C	0084C	0094C
300	1074C	1084C	1094C
600	2074C	2084C	2094C
900	7074C	7084C	7094C
1500	3074C	3084C	3094C

Forged globe valves ASME Classes 900-2500 and Inclined cast globe valves ASME Classes 900–2500 also available

SIZE		ASM	E CLAS	SS 150			ASM	E CLAS	SS 300	)		ASME	CLAS	S 600			ASME	CLAS	S 900			ASME	CLAS	S 1500	
NPS DN	Α	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	Α	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	Α	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	Α	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε	Α	<b>B</b> <sup>(1)</sup>	<b>C</b> <sup>(1)</sup>	D	Ε
2 50	8 203	16.85 428	20.88 530	2 51	8 203.2	10.50 267	16.85 428	20.88 530	2 51	8 203	11.50 292	17.10 434	21.13 537	2 51	10 254	14.50 368	19.75 502	25 635	1.65 42	18 457	14.50 368	19.75 502	25 635	1.65 42	18 457
2½ 65	8.50 216	17.10 434	21.25 540	2.50 64	10 254	11.50 292	17.10 434	21.25 540	2.50 64	10 254	13 330	18.67 474	22.88 581	2.20 56	10 254	-	_	-	_	-	-	-	-	-	-
3 80	9.50 241	18.42 468	22.75 578	3 76	10 254	12.50 318	18.42 468	22.75 578	3 76	10 254	14 356	20.19 513	24.13 613	3 76	14 356	15 381	24.09 612	30.50 775	2.71 69	14(2)(3) 356	18.50 470	24.09 612	30.50 775	2.48 63	14(2)(3) 356
4 100	11.50 292	20.88 530	26.18 665	4 102	14 356	14 356	20.88 530	26.18 665	4 102	14 356	17 432	23.88 607	29.25 743	3.54 90	24(2)(3) 610	18 457	27.50 699	35.38 899	3.54 90	18 457	21.50 546	27.42 696	35.38 899	3.26 83	-
6 150	16 406	25.75 654	32 813	6 152	24 610	17.50 445	26.38 670	32.88 835	5.31 135	24(2)(3) 610	22 559	31.22 793	37.88 962	5.31 135	24(2)(3) 610	24 610	39.13 939	45.03 1143	5.18 132	(4)		•	-E	-	
8 200	19.50 495	30.73 780	38.38 975	8 203	24 610	22 559	32 813	38.88 988	7.17 182	24 <sup>(2)or(4)</sup> 610	26 660	41.75 1060	57.88 1470	7.17 182	(4)	29 737	50.13 1273	62.63 1590	6.76 172	(4)					
10 250	24.50 622	39.25 997	46.75 1187	8.82 224	24(2)(3) 610	24.50 622	42.34 1075	52.18 1325	8.82 224	24 <sup>(2)or(4)</sup> 610	31 787	47.16 1198	59 1499	8.74 222	(4)	33 838	59.38 1508	75.65 1922	8.45 215				I.		B, C
12 300	27.50 699	42.52 1080	53 1346	12 305	24 <sup>(2)or(4)</sup> 610	28 711	46.19 1173	62.75 1594	10.81 275	(4)	33 838	57.53 1461	72.16 1833	9.84 250	(4)									1	в, с
14 350	31 787	54.21 1377	65.44 1662	13.25 337	(4)	33 838	54.21 1377	72 1829	11.93 303	(4)	-			Se	e pag	je 22-	-23				↓			Ŀ	
16 400	36 914	59.94 1522	72.63 1845	15.25 387	(4)	34 863	59.94 1522	76 1930	13.73 349	(4)	-		for	valv	e wei	ghts	and C	γs.			D A	2			-
18 450	38.50 978	59.62 1514	75 1905	17.50 444	(4)	38.50 978	59.62 1514	75 1905	15.53 394													Canto	- A -	)	▶
24 600	51 1295	85 2159	119 3023	21.21 539	(4)	55 1397	85 2159	119 3023	20.93 532													Cente Disma			


Height does not include actuators. (2) Impactor handwheel.
 Gear actuator is optional. (4) Gear actuator.

### **VELAN CAST STEEL API 594 SWING CHECK VALVES**

#### **CAST CARBON, STAINLESS OR ALLOY STEEL**

NPS 2-48 (DN 50-1200), ASME CLASSES: 150-1500





#### STANDARD MATERIALS

PART		MATE	RIALS	
Body <sup>(1)</sup>	WCB	WC6	WC9	CF8M
Seat <sup>(1)(2)</sup>	CoCr alloy faced CS	CoCr alloy faced F11	CoCr alloy faced F22	CoCr alloy faced F316
Hinge pin <sup>(1)</sup>		SS 410		SS 316
Gasket <sup>(1)</sup>	Sp	iral wound stain	lless steel/graph	iite
Cover stud	Gr. B7	E	316	B8M CI. 2
Cover nut	Gr. 2H	Gi	r. 7	Gr. 8M
Cover <sup>(1)</sup>	WCB	WC6	WC9	CF8M
Washer		Commerc	ial	
Disc <sup>(1)</sup>	CA 15 or 13Cr faced WCB	CA 15 or 13Cr faced WC6	CF8M	
Disc hanger	WCB	WC6	WC9	CF8M
Disc nut	Gr. 2H	r. 4	Gr. 8M	

(1) Other materials available.

(2) Hardfaced.

For Forged steel check valves, ASME Classes 900–2500 See our on-line catalog (CAT-PS) at www.velan.com.

#### **Design features**

- Body and cover.
   Precision machined castings.
   Exclusive: Disc shaft does not penetrate body.
- **Body and cover joint.** Accurately machined, fully-enclosed gasket (gasket materials on page 4).
- Disc.

Robust one-piece construction to withstand the severe shock of check valve service. Hardfaced with 13Cr, CoCr alloy, SS 316, or Monel, ground and lapped to a mirror finish. Sizes NPS 2–6 (DN 50–150) may have solid CA 15 (13Cr) disc. SS 316 disc with CoCr alloy facing also available.

• Disc assembly.

Non-rotating disc is fastened securely to disc hanger with a lock nut and cotter pin. Disc hanger is supported on a sturdy disc carrier hinge pin of excellent bearing qualities. All parts are accessible from top for easy servicing.

• Flanges:


ASME Classes 150–300:  $\frac{1}{16}$ " raised face. ASME Classes 600–1500:  $\frac{1}{4}$ " raised face. Finish 125–250 AARH for all valves.

#### **DESIGN SPECIFICATIONS**

ITEM	APPLICABLE SPECIFICATION
General design	API 594
Wall thickness	API 594
Pressure-temperature rating	ASME B16.34
Face-to-face dimensions for butt weld and flanged valves	ASME B16.10
Flange design	ASME B16.5
Butt welding design	ASME B16.25
Materials	ASTM

See page 22 and 23 for valve weights and CVs.

CLASS	FIGURE NUMBER	CLASS	FIGURE NUMBER
150	0114C	900	7114C
300	1114C	4500	01110
600	2114C	1500	3114C



Other sizes on application.

#### CHECK VALVE DIMENSIONS


SIZE	A	SME CL	ASS 15	0	A	SME CI	.ASS 30	0	A	SME CL	.ASS 60	0	A	SME CL	ASS 90	0	A	SME CL	ASS 150	)0
NPS DN	A	В	C	D	Α	В	C	D	A	В	C	D	Α	В	C	D	A	В	C	D
2 50	8 203	5.75 146	2 51	6.75 171	10.50 267	6 152	2 51	6.75 171	11.50 292	6.25 159	2 51	6.75 171	14.50 368	9.50 241	1.88 48	8.63 219	14.50 368	9.50 241	1.88 48	8.63 219
2½ 65	8.50 216	6.25 159	2.50 64	6.75 171	11.50 292	6.25 159	2.50 64	6.75 171	13 330	6.50 165	2.50 64	7.50 191	16.50 419	10 254	2.25 57	9.25 235	16.50 419	10 254	2.25 57	9.25 235
3 80	9.50 241	7.75 197	3 76	8.50 216	12.50 318	7.75 197	3 76	8.50 216	14 356	8.75 222	3 76	9.75 248	15 381	10.50 267	2.88 73	10.50 267	18.50 470	11.50 292	2.75 70	10.50 267
4 100	11.50 292	8.75 222	4 102	10.25 260	14 356	8.75 222	4 102	10.25 260	17 432	9.25 235	4 102	12 305	18 457	11.75 299	3.88 99	12.25 311	21.50 546	12 305	3.63 92	12.25 311
6 150	14 356	10.75 273	6 152	12.50 318	17.50 445	10.75 273	6 152	12.50 318	22 559	11.50 292	6 152	15.75 400	24 610	15 381	5.75 146	15.25 387	27.75 705	16.50 419	5.38 137	16 406
8 200	19.50 495	12.75 324	8 203	15.75 400	21 533	12.75 324	8 203	15.75 400	26 660	13.50 343	7.88	15.75 400	29 737	19.25 489	7.50 191	18.38 467	32.75 832	21 533	7 178	20.75 527
10 250	24.50 622	15.50 394	10 254	18.50 470	24.50 622	16.25 413	10 254	18.50 470	31 787	16.75 425	9.75 248	19.50 495	33 838	21.98 558	9.38 238	22.25 565	39 991	23.93 608	8.75 222	22.75 578
12 300	27.50 699	17 432	12 305	20.50 521	28 711	17 432	12 305	20.50 521	33 838	18.50 470	11.75 298	22.50 572	_	-	_	-	-	-	_	-
14 350	31 787	19.63 499	13.25 337	23 584	33 838	19.63 499	13.25 337	23 584	35 889	20.93 532	12.88 327	26.25 667	-	-	_	-	-	-	-	-
16 400	34 864	22 559	15.25 387	26.50 673	34 864	22.50 572	15.25 387	26.50 673	39 991	23.38 594	14.75 375	28.25 718	-	-	_	-	-	-	_	-
18 450	38.50 978	25 635	17.13 435	28.50 724	38.50 978	25 635	17.13 435	28.50 724	43 1092	28.67 728	16.50 419	31.50 800	-	-	-	-	-	-	_	-
20 500	38.50 978	26.50 673	19 483	31.50 800	40 1016	26.50 673	19 483	31.50 800	47 1194	27.12 689	18.25 464	35.25 895	52 1320	34.95 887	17.50 444	37.25 946	-	_	_	
24 600	51 1295	31.25 794	23.25 591	37 940	53 1346	31.25 794	23.25 591	37 940	55 1397	35.69 907	22 559	40.25 1022	_	-	_	-	-	-	_	
26 650	51 1295	32.63 829	25 635	37.25 946	-	-	-	-	57 1448	38.49 980	23.75 603	44 1118	-	-	-	-	-	-	_	-
28 700	57 1448	36.55 928	27 686	42 1067	59 1499	36.55 928	27 686	42 1067	-	_	-	-	_	-	_	-	-	-	_	-
30 750	60 1524	36.89 937	29.25 743	44.50 1130	-	-	-	_	-	_	_	-	-	-	_	-	-	-	_	-
32 800	64 1626	40.30 1026	30.75 781	47.25 1200	-	-	-	-	-	_	_	-	70 1778	47.56 1280	25.25 641	50 1270	-	-	_	-
34 850	_	-	-	-	64 1626	42.38 1076	32.75 832	48.75 1238	-	_	_	-	_	-	_	-	-	-	_	-
36 900	77 1956	41.78 1061	35.25 895	53 1346	-	-	_	_	-	_	_	-	-	-	-	-	-	-	_	-
38 950	80 2032	47.01 1194	36.63 930	53 1346	-	-	-	-	-	_	_	-	81.50 2070	50.38 1280	30 762	57 1448	-	-	_	-
42 1050	78 1981	49.72 1263	37.88 962	63.50 1613	78 1981	53.22 1352	37.88 962	63.50 1613	-	_	_	-	_	-	_	-	-	-	_	-
48 1200	94 2388	55 1397	46 1168	61 1549	-	-	-	_	-	-	-	-	_	-	_	-	-	-	_	-

### **VELAN SPECIAL SERVICES**



### **HYDROFLUORIC (HF) ACID PROCESSING VALVES**

Hydrofluoric acid is a highly corrosive acid. Industries using HF acid in their manufacturing process have placed an increasing emphasis on safety in using this product.



### HF ACID GATE, GLOBE, AND CHECK VALVES CARBON STEEL AND MONEL, NPS 2–36 (DN 50–900)


PRESSURE CLASSES: 150-600

Fugitive emissions are a critical factor in the performance of any HF acid valve and at Velan, we have been committed to reducing emissions beyond the industry standards, and providing the highest quality products to our customers for over 60 years. Velan offers a comprehensive line of Phillips-approved and UOP-listed HF acid gate, globe, and check valves with several benefits.

#### **Design features**

- **Carbon steel bonnets** delivered with Nickel weld overlay on backseat in stem hole to combat severe alkylation conditions.
- HF acid detecting paint to ensure valve integrity.
- **Stem** made from aged hardened Monel K500 for increased strength and durability. **Rising stem** makes for easy visibility for open-close indications.
- **Casting design** X ray "RT" quality castings as per B16.34 acceptance standards.
- High pressure Helium gas test. In addition to API 598, featuring more stringent allowable leakage rates, each cast valve is subjected to a high pressure Helium gas test to ensure the valve integrity, as per ISO 15848-2.
- **Dual Nickel weld layers** in seat recess area coupled to single seal welded Monel seat ring ensuring, extended strength, corrosion resistance, and long term cost of ownership.
- Body/bonnet wall thickness to API 600.
- Velan's low-fugitive emissions guarantee.
   Based on EPA Fugitive emissions regulations, API 624, ISO 15848 as well as TA-LUFT.


#### **Optional design features**




For more information on Velan HF Acid gate, globe and check valves see our on-line catalog (CAT-HFA) at www.velan.com

### **VELAN SPECIAL SERVICES**

#### **CAST STEEL CRYOGENIC VALVES**





#### CAST CRYOGENIC GATE, GLOBE, AND CHECK VALVES AUSTENITIC STAINLESS STEEL, NPS 2–30 (DN 50–750)

PRESSURE CLASSES: 150–1500

The production, transport, and storage of liquefied gases such as oxygen, nitrogen, argon, natural gas, hydrogen, or helium (down to -425°F/ -253.9°C) presents several technical problems. Velan specially-adapted extended bonnet cast valves offer safe and efficient service.

#### **Materials**

- Body and bonnet: Austenitic stainless steel castings used for bodies and bonnets offer excellent impact strength, minimal heat loss, and protection against corrosion.
- Stem: Austenitic stainless steel. To reduce galling, stems are also offered in A479 grade XM-19 with high toughness even at extreme low temperatures, excellent low friction, and galling-free movement at points of stem contact.
- Wetted parts: all Austenitic stainless steel and CoCr alloy.
- Stem nut/yoke bushing: Austenitic ductile iron Gr. D-2C.
- **Packing:** PTFE or graphite packing protected from freezing by a column of insulating gas.
- Seating faces: CoCr alloy is used to prevent seizing and galling. When extremely tight shutoff is required, globe and check valves are supplied with Neoflon, PTFE, or other soft inserts.
- Bolting: Strain-hardened Austenitic stainless steel.
- Lubrication of stem nut: Exxon Nebula Lubriplate No. 930-AA or Shell Darina EPI or equivalent.

#### **Design features**

- **Extended bonnets** with sufficient gas column length, usually specified by customer, are supplied for all valves to keep the stem packing at sufficient distance away from the cold fluid to remain functional.
- Flexible wedges with CoCr alloy seating faces for cryogenic service.
- Neoflon inserts are available for globe, piston, and swing check discs.
- **Cleaning:** All cryogenic valves are thoroughly degreased and cleaned and pipe ends are sealed to prevent contamination.


For more information on cryogenic valves see our on-line catalog (VEL-CRYO) at www.velan.com.

#### TABLE OF LIQUEFIED GASES

Tana	Boiling	g point	Liquid	T	Boiling	point	Liquid	
Туре	°C	°F	density lb / ft.³	Туре	°C	°F	density lb / ft.₃	
Natural gas (LNG)	-168	-270	26	Air	-194.4	-318	57.87	
Methane (CH₄)	-161.5	-258	26.20	Nitrogen (N <sub>2</sub> )	-195.8	-320	50.45	
Oxygen (0₂)	-182.9	-296	71.20	Hydrogen(H₂)	-252.7	-423	4.43	
Argon (Ar)	-185.9	-303	87.40	Helium (He)	-268.9	-452	7.82	
Carbon dioxide (CO <sub>2</sub> )	-78.5	-109	50.60	Absolute zero	-273.16	-460	-	

### **VELAN SPECIAL SERVICES**

#### BLOCK AND BLEED GATE VALVES FOR CHEMICAL AND PETROCHEMICAL INDUSTRIES



Valve shown above has a special "Pipeline" bonnet. Standard bonnets with regular yoke also available.



#### CAST STEEL API 600\* BLOCK AND BLEED GATE VALVES ASME CLASS: 150, NPS 2–60 (DN 50–1500) ASME CLASS: 300, NPS 2–36 (DN 50–900)

FLANGED OR BUTT WELD ENDS


#### **Design features**

- Positive shutoff with visual or remote proof of seat tightness.
- No product contamination due to absolute tightness.
- **Dual seating.** Elastomer-to-metal seat plus metal-to-metal secondary seal.
- Fire safe. The metal-to-metal seat ensures tightness if the secondary elastomer seat is damaged during the fire.
- **PTFE seat insert** resists corrosive media, has high abrasion resistance, and operates up to +400°F (204°C).
- Seat hardfaced with SS 410 and seal welded.

#### Easy in-line valve reseating

Seats are hardfaced with SS 410 and welded-in for lifetime service. A worn soft seat insert can easily be replaced after removal of the wedge from the body. Shut off flow and relieve pressure before replacing the seat insert.

#### Seat/wedge design



#### **Cavity over-pressurization protection**

Block and bleed valves are capable of trapping fluid in the cavity between the seats when in the closed position. If subjected to an increase in temperature, an excessive build up of pressure can occur, which may result in a pressure boundary failure. It is the responsibility of the user to assure that measures are taken to prevent the pressure from exceeding the rating of the valve.

Cavity over-pressurization protection is not provided by Velan, unless specified. Velan can provide alternative solutions to safeguard against cavity overpressurization. Please contact us to determine the correct solution for your use.

(1) For gate valves larger than NPS 42 (DN 1050), in pressure class 150 and 300, and gate valves larger than 24" in pressure classes 600 and greater, wall thickness is based on B16.34 plus additional wall thickness allowance.

### **GEAR, ELECTRIC, AND CYLINDER ACTUATORS**

#### **Gear actuators**

Gearing is generally applied to valves to make operation easier. The gearing may be, of the spur, bevel, or worm type—any of which may be applied to Velan valves.



The gears and gear brackets may be either cast iron or cast steel

and may have cast or cut teeth, depending on the loads and the application. Gearing is too often neglected when valve operation is considered, resulting in unsatisfactory operation that requires expensive changes.

YPE	Size		Optional	St	andard
T	ASME Class	NPS	DN	NPS	DN
	150	6–24	150-600	30-60	750–1500
<u>ш</u>	300	6–16	150-400	18-36	450-900
GATI	600	4–12	100-300	14-36	350-900
0	900	3–6	80–150	8–10	200-250
	1500	3–4	80–100	6–10	150-250
	150	6–12	150–300	14–16	350-400
B	300	6–12	150-300	14–16	350-400
	600	4–10	100-250		—
6	900	2–4	50-100	_	_
	1500	2–4	50-100		

#### **Electric actuators**

Motorized controls may be applied to valves of almost any size for operation in practically any position or location.

All units, whether installed

directly on a valve or on a floor stand, **m** can be manually operated in case of power failure. The units are available for either alternating or direct current.

Motor units supplied by Velan are the high-torque type with windings impregnated to resist both oil and moisture. They are completely weather-proof, explosionproof (optional), and dust and steam tight. Various sizes and styles are available for different applications, and systems and can be varied to fit special requirements.

#### **Cylinder actuators**

The most commonly used cylinders are actuated by air, but oil and water types are also available if required. In all designs, the valve stem normally serves as a piston rod with the disc fastened directly to it. Tail rods are also supplied as standard equipment to serve



as position indicators and for emergency opening. Handwheels and gear heads can be mounted on top of cylinders for operation in an emergency, which may arise due to the loss of operating medium in the cylinder.

Velan cylinders can be furnished with mounting pads for one of the commercial cylinders or valve positioners that provide throttling control. High-pressure cylinders are also available for specific applications.

#### Valve actuator sizing

The Velan philosophy for selecting an actuator is to calculate the required thrust and torque to operate the valve at the required service conditions. A reasonable margin of excess actuator capability over that required is always allowed for in the final actuator selection, but grossly oversized actuators are avoided.

Because of the wide variations in system operating conditions, actuator sizing is based on the following:

Actuator type	Line pressure	Differential pressure (closed)	Power supply
Electric	Specified by customer	Specified by customer	Voltage, type, phase, specified by customer
Pneumatic	Specified by customer	Specified by customer	Air pressure specified by customer
Hydraulic	Specified by customer	Specified by customer	Hydraulic pressure specified by customer
Handwheel gear actuated	70% of CWP <sup>(1)</sup> unless otherwise advised by customer	70% of CWP <sup>(1)</sup> unless otherwise advised by customer	200 lb. rimpull <sup>(2)</sup> unless otherwise advised by customer

(1) CWP = cold working pressure per ASME B16.34 at 100°F.

(2) Rimpull is defined as the total tangential force acting on the outer rim of the handwheel (e.g., 200 lb rimpull requires 100 lb force per hand). This rimpull figure is given for closing/opening conditions. For running conditions (travel from open to closed or vice versa), the rimpull is considerably less. For details, contact the company.

### **OTHER ACCESSORIES**

#### **Chain wheels**

Chainwheels are used to enable remote actuation of a valve that is typically at a higher elevation than the person operating it. Chainwheels may be used on Velan cast steel valves covered in this catalogue. Velan strongly recommends the use of appropriately designed safety accessories to prevent the risk of the chainwheel falling in the event it becomes detached from the valve assembly. Please contact Velan for additional information on the correct application of chainwheels on our valves.

#### **Floor stands**

Floor stands are available in a number of sizes, and the size to be used depends on the stem size and stem load of the valve.

#### Lifting points

Lifting points are available to facilitate handling of larger and heavier valves.

### **BYPASSES**


#### AVAILABLE FOR ALL VELAN CAST STEEL VALVES IN ACCORDANCE WITH MSS-SP45 - SERIES A

#### **API 600 GATE** (*Note: Dimensions are in inches*)

SI	ZE		CLAS	S 15	0		CLAS	S 300			CLAS	S 60	0
NPS	DN	Bypass	A	Elbow	В	Bypass	A	Elbow	В	Bypass	A	Elbow	В
3	80	1/2	10.50	1/2	4.75	1/2	12.25	1/2	6.25	1/2	12.31	1/2	6.25
4	100	1/2	13.00	1/2	5.63	1/2	13.00	1/2	6.50	1/2	14.00	1/2	6.50
6	150	3/4	14.00	3/4	6.13	3/4	14.00	3/4	9.00	3/4	15.00	3/4	9.00
8	200	3/4	17.00	3/4	6.81	3/4	17.00	3/4	10.00	3/4	17.38	3/4	10.00
10	250	1	18.00	1	7.69	1	18.00	1	11.00	1	18.50	1	11.00
12	300	1	18.00	1	8.13	1	18.00	1	12.50	1	18.50	1	12.50
14	350	1	23.00	1	9.00	1	18.50	1	16.00	1	18.50	1	19.13
16	400	1	24.00	1	10.00	1	18.50	1	15.50	1	20.50	1	20.00
18	450	1	26.63	1	12.00	1	19.50	1	14.00	1	20.50	1	24.00
20	500	1	26.63	1	12.00	1	19.50	1	16.00	1	20.50	1	24.00
24	600	1	28.75	1	12.25	1	22.50	1	18.25	1	22.50	1	32.00
30	750	1	33.63	1	14.00	1	26.00	1	24.00	1	27.00	1	36.00
34	850	—	—	_		—	—	_	—	—	28.00	1	42.38
36	900	1	34.00	1	15.25	1	28.00	1	50.00	1	30.00	1	35.00
38	950	—	—	_	_	—	—	_	—	—	31.00	1	47.38
40	1000	—	—	_	_	—	32.00	_	45.00	—	32.00	1	50.50
42	1050	—	—	—	—	—	32.00		45.00	—	—	—	—
44	1100	_	—	_		_		_	—		35.00	_	50.00
50	1250	—		—	_	—		_	—	—	39.00	_	61.75
60	1500	1	44.00	1	24.00	—	_	—	—	_	_	—	—

#### **API 623 GLOBE** (Note: Dimensions are in inches)


SI	ZE CLASS 150						CLAS	)	CLASS 600				
NPS	DN	Bypass	A	Elbow	В	Bypass	A	Elbow	В	Bypass	A	Elbow	В
3	80	1/2	13.00	1/2	6.38	1/2	11.50	<sup>1</sup> /2	6.13	1/2	13.00	1/2	8.25
4	100	1/2	13.00	1/2	7.50	1/2	16.50	<sup>1</sup> /2	7.00	1/2	15.00	1/2	9.50
6	150	3/4	11.13	3/4	11.00	3/4	14.75	3/4	11.00	3/4	13.00	3/4	11.00
8	200	3/4	11.50	3/4	14.00	3/4	13.00	3/4	14.00	3/4	13.00	3/4	11.25
10	250	1	18.00	1	14.88	1	18	1	15.00	_		_	_
12	300	1	18.00	1	19.00	1	18	1	18.00	_		_	
14	350	1	18.00	1	19.50	1	18	1	19.50	_	_	_	_
16	400	1	18.00	1	24.00	1	18	1	24.00	_	_	_	



#### FLANGES, WEIGHTS, AND Cv FLOW COFFICIENT S

#### **API 600 CAST STEEL VALVES CLASS 150 DRILLED AND FACED AS FOLLOWS** ASME B 16.5 and B16.47<sup>(1)</sup>

(Note: Dimensions are in inches and weights in pounds)



Bolt circle	
-------------	--

40145	DIMENSIONS IN INCHES								WEIGHT IN LBS.						CV		
ASME CLASS	SIZ	ZE	FLANGE	<b>BOLT CIRCLE</b>	HOLE	QTY.	DIAM.	G	ATE	GLO	)BE	SW	ING	FLOW	COEFFIC	ENTS	
GLASS	NPS	DN	DIAM.	DIAM.	DIAM.	HOLES	BOLTS	BW	FL	BW	FL	BW	FL	GATE	GLOBE	CHECK	
	2	50	6.00	4.75	0.75	4	5/8	42	48	48	55	31	40	260	35	95	
	<b>2</b> <sup>1</sup> / <sub>2</sub>	65	7.00	5.50	0.75	4	5/8	50	59	54	58	35	44	420	60	150	
	3	80	7.50	6.00	0.75	4	5/8	67	78	82	102	59	78	625	92	220	
	4	100	9.00	7.50	0.75	8	5/8	97	117	120	152	98	121	1150	180	410	
	6	150	11.00	9.50	0.88	8	3/4	180	198	240	280	179	212	2650	430	950	
	8	200	13.50	11.75	0.88	8	3/4	278	319	405	435	314	360	4850	810	1750	
	10	250	16.00	14.25	1.00	12	7/8	456	515	500	550	513	586	7750	1070	2800	
	12	300	19.00	17.00	1.00	12	7/8	646	738	1050	1200	602	823	11,500	1950	4100	
	14	350	21.00	18.75	1.13	12	1	875	954	1700	1850	765	960	14,000	2500	6200	
	16	400	23.50	21.25	1.13	16	1	1120	1200	2300	2500	1120	1300	19,000	3400	8400	
	18	450	25.00	22.75	1.25	16	11/8	1485	1570	2640	2850	1450	1660	24,000	4500	11,000	
	20	500	27.50	25.00	1.25	20	11/8	1825	1910			1700	2050	31,000		13,500	
150	24	600	32.00	29.50	1.38	20	11/4	2870	2960	7035	7403	2900	3300	45,000	6720	20,000	
1/16	26(1)	650	34.25	31.75	1.38	24	11/4	3600	3700		_	3600	4000	53,000	—	23,500	
RAISED	28(1)	700	36.50	34.00	1.38	28	11/4	4400	4500		_	4300	5000	62,000	—	28,000	
FACE	30(1)	750	38.75	36.00	1.37	28	11/4	4705	4750		—	6300	7000	73,000	—	33,000	
TAUL	32(1)	800	41.75	38.50	1.63	28	11/2	5800	6000		—	6000	6600	81,000	—	36,245	
	34(1)	850	43.75	40.50	1.63	32	1½		6000		_			92,500	—		
	36(1)	900	46.00	42.75	1.63	32	1½	6500	6850		_	8500	9500	108,000	—	48,000	
	38 <sup>(1)</sup> 40 <sup>(1)</sup>	950	48.75	45.25	1.63	32 36	1½ 1½	8857	9674		_	_		115,000	—		
	40 <sup>(1)</sup> 42 <sup>(1)</sup>	1000 1050	50.75 53.00	47.25 49.50	1.63 1.63	36	1/2	8400 10,000	9000 11.000					130,000	—		
		1150	57.25	<u>49.50</u> 53.75	1.63	40	1/2 1/2	14,000	15,719					142,000			
	40 (1)	1200	59.50	56.00	1.63	40	1/2 1/2	14,000	15,000					190,000			
	50 <sup>(1)</sup>	1250	56.81	54.56	1.03	44	1/2	14,000	8775					198,000			
	54 <sup>(1)</sup>	1350	66.25	62.75	1.25	44	1/8 1 <sup>3</sup> /4	21,000	23,000					238,000			
	54 <sup>(1)</sup>	1400	68.75	65.00	1.88	44	174 13/4	21,000	20,000					260,000			
	60 <sup>(1)</sup>	1500	73.00	69.25	1.88	52	174 1 <sup>3</sup> /4	22,600	26,600					300,000			
	64 <sup>(1)</sup>	1600	75.00		1.00		1/4		29,000		_			340,000			

(1) NPS 26 (DN 650) and up: ASME B16.47 Series A (MSS-SP-44). For Series B (API 605) contact the factory.

### FLANGES, WEIGHTS, AND Cv FLOW COFFICIENTS

#### API 600 CAST STEEL VALVES CLASS 300, 600, 900, AND 1500 DRILLED AND FACED AS FOLLOWS

ASME B 16.5 and B16.47<sup>(1)</sup>


ACME

(Note: Dimensions are in inches and weights in pounds)

DIMENSIONS IN INCHES



WEIGHTINIDE



CV

ASME	DIMENSIONS IN INCHES								WEIGHT IN LBS.						CV		
CLASS	SI	ZE	FLANGE	<b>BOLT CIRCLE</b>	HOLE	QTY.	DIAM.	GA	TE	GL	OBE	SW	ING	FLOW (	COEFFICI	ENTS	
	NPS	DN	DIAM.	DIAM.	DIAM.	HOLES	BOLTS	BW	FL	BW	FL	BW	FL	GATE	GLOBE	CHECK	
	2	50	6.50	5.00	0.75	8	5/8	46	60	45	60	37	45	260	35	95	
	<b>2</b> <sup>1</sup> / <sub>2</sub>	65	7.50	5.88	0.88	8	3/4	55	76	63	72	49	57	420	60	150	
	3	80	8.25	6.62	0.88	8	3/4	90	115	88	114	70	96	625	92	220	
	4	100	10.00	7.88	0.88	8	3/4	136	166	130	171	110	150	1150	180	410	
	6	150	12.50	10.63	0.88	12	3/4	245	314	261	337	204	265	2650	370	950	
	8	200	15.00	13.00	1.00	12	3/4	415	506	447	565	360	455	4850	695	1750	
	10	250	17.50	15.25	1.13	16	1	646	762	1000	1150	582	650	7750	1065	2800	
000	<u>12</u> 14	300 350	20.50 23.00	17.75 20.25	1.25 1.25	16 20	1½ 1½	900 1392	1100 1720	1300 1800	1550 2100	825 1200	945 1350	11,500 14,000	1640 2015	4100 6200	
300	14	400	25.50	22.50	1.25	20	1/8 11/4	1870	2220	2300	2700	1500	1800	19,000	2015	8400	
1/16	18	450	28.00	24.75	1.38	20	11/4	2405	2960	2640	3200	2000	2400	23,500	4500	11,000	
RAISED	20	500	30.50	27.00	1.38	24	11/4	3260	3700			2600	3000	30,000		13,500	
FACE	24	600	36.00	32.00	1.63	24	11/2	4250	5100	7109	7995	3000	4050	44,000	6580	20,000	
	26(1)	650	38.25	34.50	1.75	28	1%	5000	5500		_	_	_	53,000	_		
	28(1)	700	40.75	37.00	1.75	28	15/8	7000	7500		_	5000	6000	62,000		28,000	
	30(1)	750	43.00	39.25	1.88	28	13/4	8550	9000		—	_		73,000	—	—	
	32(1)	800	45.25	41.50	2.00	28	11/8	8200	8800	—	—	—	—	81,000	—	—	
	34(1)	850	—	—	—	—	—	_	—	_	—	8350	10,100		—	41,330	
	36(1)	900	50.00	46.00	2.13	32	2	13,500	15,500	—	—	—	—	108,000	—	—	
	40(1)	1000	48.75	45.50	1.75	32	15/8	14,500	16,200				—	129,500			
	42(1)	1050	50.75	47.00	1.75	32	15/8	14,500	17,000					129,500			
	2	50	6.50	5.00	0.75	8	5/8	60	72	60	72	48	52	260	35	95	
	2 <sup>1</sup> / <sub>2</sub>	65	7.50	5.88	0.88	8	3/4 3/	89	102	89	100	59	87	420	30	150	
	3	80 100	8.25 10.75	6.63 8.50	0.88	8	3/4 7/8	130 224	157 275	130 213	150 285	96 167	130 225	625 1150	92 155	220 410	
	6	150	14.00	11.50	1.13	12	1	394	540	415	515	332	476	2650	369	950	
	8	200	16.50	13.75	1.15	12	11/8	726	884	1050	1220	525	715	4850	695	1750	
	10	250	20.00	17.00	1.38	16	11/8	1125	1405	1550	1830	1000	1250	7750	1050	2800	
	12	300	22.00	19.25	1.38	20	11/4	1490	1812			1500	1750	11,500	1345	4100	
600	14	350	23.75	20.75	1.50	20	13/8	2200	2500	_	_	1750	2050	13,000		5900	
	16	400	27.00	23.75	1.63	20	11/2	3000	3700		_	2400	3100	18,000		7800	
1/4 RAISED	18	450	29.25	25.75	1.75	20	15%	4000	4800		—	3200	4000	22,000	—	9900	
	20	500	32.00	28.50	1.75	24	1%	5600	6800	_	—	4500	6100	27,000	—	12,000	
FACE	24	600	37.00	33.00	2.00	24	11/8	8000	9800			6400	7600	40,000		18,000	
	26	650						6835	8154			7600	8930	38,000		21,150	
	30(1)	750	44.50	40.25	2.13	28	2	12,000	14,000		—		—	52,000			
	34 <sup>(1)</sup> 36 <sup>(1)</sup>	850	49.00	44.50	2.38	28	21/4	17.000	19,000					82,500			
	36(1)	900 950	51.75 50.00	47.00 45.75	2.63	28 28	2½ 2¼	17,000	19,500 26,700					72,000			
	40(1)	1000	50.00	45.75	2.38 2.38	32	2/4 21/4		33,200					115,000			
	40(1)	1100	52.00	52.50	2.63	32	2/4 2 <sup>1</sup> / <sub>2</sub>		42,800					144,000			
	50 <sup>(1)</sup>	1250	65.75	60.00	3.13	28	3	_	59,100					190,000	_	_	
	2	50	8.50	6.50	1.00	8	7/8	150	185	68	150	135	165	230	30	80	
	<b>2</b> <sup>1</sup> / <sub>2</sub>	65	9.63	7.50	1.13	8	1	_	_		_	175	210		_	200	
	3	80	9.50	7.50	1.00	8	7/8	235	270	165	225	175	210	560	90	200	
	4	100	11.50	9.25	1.25	8	11/8	270	355	260	350	245	330	1050	155	380	
900	6	150	15.00	12.50	1.25	12	11/8	830	980	641	831	485	635	2400	350	875	
1/4	8	200	18.50	15.50	1.50	12	13/8	1220	1500	1278	1588	700	900	4200	610	1325	
RAISED	10	250	21.50	18.50	1.50	16	1%	2000	2400	—		1600	2100	6750	975	2400	
FACE	12	300	24.00	21.00	1.50	20	1%	3170	3670		—		—	9700	—	—	
	14	350	25.25	22.00	1.62	20	1½	3900	4460					12,000			
	16 20	400 500	27.75 33.75	24.25 29.50	1.75 2.13	20 20	1% 2	5570	6250			<u> </u>	7081	16,000		11177	
	32	800	51.75	45.50	3.38	20	2 3¼					5961 13674	18368			24036	
	32	950		45.50	3.30	20	374					20,250	26,800			34,500	
	2	50	8.50	6.50	1.00	8	7/8	150	185	68	150	135	165	230	30	80	
1500	2 <sup>1</sup> /2	65	9.63	7.50	1.13	8	1					205	275			185	
1500	3	80	10.50	8.00	1.25	8	11/8	255	325	188	274	205	275	510	75	185	
1/4	4	100	12.25	9.50	1.37	8	11/4	430	520			340	430	925	130	330	
RAISED	6	125	15.50	12.50	1.50	12	1¾	1045	1205	—	—	805	965	2100	—	750	
FACE	8	200	19.00	15.50	1.75	12	1%	1850	2550		—	1350	2050	3650	—	1325	
	10	250	23.00	19.00	2.00	12	11%	2600	3300	—	—	2233	2821	5850	—	2103	

(1) NPS 26 (DN 650) and up: ASME B16.47 Series A (MSS-SP-44). For Series B (API 605) contact the factory.

### PRESSURE-TEMPERATURE RATINGS (psig – °F)

#### STANDARD CLASS VALVES FLANGED AND BUTT WELD END

NOTE: FOR SPECIAL CLASS VALVES, WHICH HAVE HIGHER RATINGS CONTACT THE COMPANY.

#### **CAST ASTM MATERIAL STANDARD – TO ASME B16.34**

ASME Boiler and Pressure Vessel Code Section II materials that also meet the requirements of the listed ASTM specifications. psig/°F (bar/°C) Classes 150-4500

#### A 216 Gr. WCB<sup>(1)</sup>

TEMP.		WORKING PRESSURES BY CLASS, psig											
°F	150	300	600	900	1500	2500	4500						
-20 to 100	285	740	1,480	2,220	3,705	6,170	11,110						
200	260	680	1,360	2,035	3,395	5,655	10,185						
300	230	655	1,310	1,965	3,270	5,450	9,815						
400	200	635	1,265	1,900	3,170	5,280	9,505						
500	170	605	1,205	1,810	3,015	5,025	9,040						
600	140	570	1,135	1,705	2,840	4,730	8,515						
650	125	550	1,100	1,650	2,745	4,575	8,240						
700	110	530	1,060	1,590	2,665	4,425	7,960						
750	95	505	1,015	1,520	2,535	4,230	7,610						
800	80	410	825	1,235	2,055	3,430	6,170						
850	65	320	640	955	1,595	2,655	4,785						
900	50	230	460	690	1,150	1,915	3,455						
950	35	135	275	410	685	1,145	2,055						
1,000	20	85	170	255	430	715	1,285						

#### A 217 Gr.WC6<sup>(3)(4)(5)</sup>

TEMP.		WORK	NG PRE	SSURE	S BY CLA	SS, psi	g
°F	150	300	600	900	1500	2500	4500
-20 to 100	290	750	1,500	2,250	3,750	6,250	11,250
200	260	750	1,500	2,250	3,750	6,250	11,250
300	230	720	1,445	2,165	3,610	6,015	10,830
400	200	695	1,385	2,080	3,465	5,775	10,400
500	170	665	1,330	1,995	3,325	5,540	9,965
600	140	605	1,210	1,815	3,025	5,040	9,070
650	125	590	1,175	1,765	2,940	4,905	8,825
700	110	570	1,135	1,705	2,840	4,730	8,515
750	95	530	1,065	1,595	2,660	4,430	7,970
800	80	510	1,015	1,525	2,540	4,230	7,610
850	65	485	975	1,460	2,435	4,060	7,305
900	50	450	900	1,350	2,245	3,745	6,740
950	35	320	640	955	1,595	2,655	4,785
1,000	20	215	430	650	1,080	1,800	3,240
1,050	20(a)	145	290	430	720	1,200	2,160
1,100	20(a)	95	190	290	480	800	1,440
1,150	20(a)	65	130	195	325	545	975
1,200	15(a)	40	80	125	205	345	615
(a) Flanged	d-end v	alve r	atinas	termin	ate at 1.	000°F.	

#### A217 Gr. WC9 (3) (4) (5)

TEMP.	١	WORKING PRESSURES BY CLASS, psig											
°F	150	300	600	900	1500	2500	4500						
-20 to 100	290	750	1,500	2,250	3,750	6,250	11,250						
200	260	750	1,500	2,250	3,750	6,250	11,250						
300	230	730	1,455	2,185	3,640	6,070	10,925						
400	200	705	1,410	2,115	3,530	5,880	10,585						
500	170	665	1,330	1,995	3,325	5,540	9,965						
600	140	605	1,210	1,815	3,025	5,040	9,070						
650	125	590	1,175	1,765	2,940	4,905	8,825						
700	110	570	1,135	1,705	2,840	4,730	8,515						
750	95	530	1,065	1,595	2,660	4,430	7,970						
800	80	510	1,015	1,525	2,540	4,230	7,610						
850	65	485	975	1,460	2,435	4,060	7,305						
900	50	450	900	1,350	2,245	3,745	6,740						
950	35	385	755	1,160	1,930	3,220	5,795						
1,000	20	265	535	800	1,335	2,230	4,010						
1,050	20(a)	175	350	525	875	1,455	2,625						
1,100	20(a)	110	220	330	550	915	1,645						
1,150	20(a)	70	135	205	345	570	1,030						
1,200	15(a)	40	80	125	205	345	615						

(a) Flanged-end valve ratings terminate at 1,000°F.

#### A 217 Gr. C5 (3) (5)

TEMP.		WORK	NG PRE	SSURE	S BY CLA	ASS, psi	g				
°F	150	300	600	900	1500	2500	4500				
-20 to 100	290	750	1,500	2,250	3,750	6,250	11,250				
200	260	750	1,500	2,250	3,750	6,250	11,250				
300	230	730	1,455	2,185	3,640	6,070	10,925				
400	200	705	1,410	2,115	3,530	5,880	10,585				
500	170	665	1,330	1,995	3,325	5,540	9,965				
600	140	605	1,210	1,815	3,025	5,040	9,070				
650	125	590	1,175	1,765	2,940	4,905	8,825				
700	110	570	1,135	1,705	2,840	4,730	8,515				
750	95	530	1,065	1,595	2,660	4,430	7,970				
800	80	510	1,015	1,525	2,540	4,230	7,610				
850	65	485	975	1,460	2,435	4,060	7,305				
900	50	375	745	1,120	1,870	3,115	5,605				
950	35	275	550	825	1,370	2,285	4,115				
1,000	20	200	400	595	995	1,655	2,985				
1,050	20(a)	145	290	430	720	1,200	2,160				
1,100	20(a)	100	200	300	495	830	1,490				
1,150	20(a)	60	125	185	310	515	925				
1,200	15(a)	35	70	105	170	285	515				

(a) Flanged-end valve ratings terminate at 1,000°F.

#### A 217 Gr. C12 (3) (5)

TEMP.		WORKI	NG PRE	SSURE	S BY CLA	SS, psi	g
°F	150	300	600	900	1500	2500	4500
-20 to 100	290	750	1,500	2,250	3,750	6,250	11,250
200	260	750	1,500	2,250	3,750	6,250	11,250
300	230	730	1,455	2,185	3,640	6,070	10,925
400	200	705	1,410	2,115	3,530	5,880	10,585
500	170	665	1,330	1,995	3,325	5,540	9,965
600	140	605	1,210	1,815	3,025	5,040	9,070
650	125	590	1,175	1,765	2,940	4,905	8,825
700	110	570	1,135	1,705	2,840	4,730	8,515
750	95	530	1,065	1,595	2,660	4,430	7,970
800	80	510	1,015	1,525	2,540	4,230	7,610
850	65	485	975	1,460	2,435	4,060	7,305
900	50	450	900	1,350	2,245	3,745	6,740
950	35	375	755	1,130	1,885	3,145	5,655
1,000	20	255	505	760	1,270	2,115	3,805
1,050	20(a)	170	345	515	855	1,430	2,570
1,100	20(a)	115	225	340	565	945	1,695
1,150	20(a)	75	150	225	375	630	1,130
1,200	20(a)	50	105	155	255	430	770

(a) Flanged-end valve ratings terminate at 1,000°F.

#### A 351 Gr. CF8M (6)

TEMP.		WORK	ING PRE	SSURE	S BY CLA	<b>SS</b> , psi	g
°F	150	300	600	900	1500	2500	4500
-20 to 100	275	720	1,440	2,160	3,600	6,000	10,800
200	235	620	1,240	1,860	3,095	5,160	9,290
300	215	560	1,120	1,680	2,795	4,660	8,390
400	195	515	1,025	1,540	2,570	4,280	7,705
500	170	480	955	1,435	2,390	3,980	7,165
600	140	450	900	1,355	2,255	3,760	6,770
650	125	440	885	1,325	2,210	3,680	6,625
700	110	435	870	1,305	2,170	3,620	6,515
750	95	425	855	1,280	2,135	3,560	6,410
800	80	420	845	1,265	2,110	3,520	6,335
850	65	420	835	1,255	2,090	3,480	6,265
900	50	415	830	1,245	2,075	3,460	6,230
950	35	385	775	1,160	1,930	3,220	5,795
1,000	20	365	725	1,090	1,820	3,030	5,450
1,050	20	360	720	1,080	1,800	3,000	5,400
1,100	20(a)	305	610	915	1,525	2,545	4,575
1,150	20(a)	235	475	710	1,185	1,970	3,550
1,200	20(a)	185	370	555	925	1,545	2,775
1,250	20(a)	145	295	440	735	1,230	2,210
1,300	20(a)	115	235	350	585	970	1,750
1,350	20(a)	95	190	290	480	800	1,440
1,400	20(a)	75	150	225	380	630	1,130
1,450	20(a)	60	115	175	290	485	875
1,500	15(a)	40	85	125	205	345	620

(a) Flanged-end valve ratings terminate at 1,000°F.

#### A 351 Gr. CF3M (7)

TEMP.		WORKI	NG PRE	SSURE	S BY CLA	ASS, psi	g
°F	150	300	600	900	1500	2500	4500
-20 to 100	230	600	1,200	1,800	3,000	5,000	9,000
200	195	510	1,020	1,535	2,555	4,260	7,670
300	175	455	910	1,370	2,280	3,800	6,840
400	160	420	840	1,260	2,100	3,500	6,300
500	150	395	785	1,180	1,970	3,280	5,905
600	140	370	745	1,115	1,860	3,100	5,580
650	125	365	730	1,095	1,825	3,040	5,470
700	110	360	720	1,080	1,800	3,000	5,400
750	110	355	705	1,060	1,765	2,940	5,290
800	80	345	690	1,035	1,730	2,880	5,185
850	65	340	675	1,015	1,690	2,820	5,075

#### General Notes:

- (1) Upon prolonged exposure to temperatures above 800°F, the carbide phase of steel may be converted to graphite. Permissible, but not recommended for prolonged use above 800°F.
- (3) Use normalized and tempered material only.
- (4) Not to be used over 1,100°F.
- (5) The deliberate addition of any element not listed in ASTM A 217, Table 1, is prohibited, except that Ca and Mg may be added for deoxidation.
- (6) At temperatures over 1,000°F, use only when the carbon content is 0.04% or higher.
- (7) Not to be used over 800°F.

### **PRESSURE-TEMPERATURE RATINGS (bars – °C)**

#### STANDARD CLASS VALVES FLANGED AND BUTT WELD END

NOTE: FOR SPECIAL CLASS VALVES, WHICH HAVE HIGHER RATINGS CONTACT THE COMPANY.

#### **CAST ASTM MATERIAL STANDARD – TO ASME B16.34**

ASME Boiler and Pressure Vessel Code Section II materials that also meet the requirements of the listed ASTM specifications. psig/°F (bar/°C) Classes 150-4500

#### A216 Gr. WCB<sup>(1)</sup>

TEMP.	WORKING PRESSURES BY CLASS, bar											
°C	150	300	600	900	1500	2500	4500					
-29 to 38	19.6	51.1	102.1	153.2	255.3	425.5	765.9					
50	19.2	50.1	100.2	150.4	250.6	417.7	751.9					
100	17.7	46.6	93.2	139.8	233.0	388.3	699.0					
150	15.8	45.1	90.2	135.2	225.4	375.6	676.1					
200	13.8	43.8	87.6	131.4	219.0	365.0	657.0					
250	12.1	41.9	83.9	125.8	209.7	349.5	629.1					
300	10.2	39.8	79.6	119.5	199.1	331.8	597.3					
325	9.3	38.7	77.4	116.1	193.6	322.6	580.7					
350	8.4	37.6	75.1	112.7	187.8	313.0	563.5					
375	7.4	36.4	72.7	109.1	181.8	303.1	545.5					
400	6.5	34.7	69.4	104.2	173.6	289.3	520.8					
425	5.5	28.8	57.5	86.3	143.8	239.7	431.5					
450	4.6	23.0	46.0	69.0	115.0	191.7	345.1					
475	3.7	17.4	34.9	52.3	87.2	145.3	261.5					
500	2.8	11.8	23.5	35.3	58.8	97.9	176.3					
538	1.4	5.9	11.8	17.7	29.5	49.2	88.6					

#### A 217 Gr.WC6<sup>(3)(4)(5)</sup>

TEMP.		WORK	ING PR	ESSURE	S BY CL	ASS, ba	r
°C	150	300	600	900	1500	2500	4500
-29 to 38	19.8	51.7	103.4	155.1	258.6	430.9	775.7
50	19.5	51.7	103.4	155.1	258.6	430.9	775.7
100	17.7	51.5	103	154.4	257.4	429	772.2
150	15.8	49.7	99.5	149.2	248.7	414.5	746.2
200	13.8	48	95.9	143.9	239.8	399.6	719.4
250	12.1	46.3	92.7	139	231.8	386.2	694.8
300	10.2	42.9	85.7	128.6	214.4	357.1	642.6
325	9.3	41.4	82.6	124	206.6	344.3	619.6
350	8.4	40.3	80.4	120.7	201.1	335.3	603.3
375	7.4	38.9	77.6	116.5	194.1	323.2	581.8
400	6.5	36.5	73.3	109.8	183.1	304.9	548.5
425	5.5	35.2	70	105.1	175.1	291.6	524.7
450	4.6	33.7	67.7	101.4	169	281.8	507
475	3.7	31.7	63.4	95.1	158.2	263.9	474.8
500	2.8	25.7	51.5	77.2	128.6	214.4	385.9
538	1.4	14.9	29.8	44.7	74.5	124.1	223.4
550	1.4(a)	12.7	25.4	38.1	63.5	105.9	190.6
575	1.4(a)	8.8	17.6	26.4	44	73.4	132
600	1.4(a)	6.1	12.2	18.3	30.5	50.9	91.6
625	1.4(a)	4.3	8.5	12.8	21.3	35.5	63.9
650	1.1(a)	2.8	5.7	8.5	14.2	23.6	42.6
(a) Elangos	landy	alvo r	atinga	tormin	ato at F	2000	

A217 Gr. WC9 (3) (4) (5)

TEMP.		WORKING PRESSURES BY CLASS, bar											
°C	150	300	600	900	1500	2500	4500						
-29 to 38	19.8	51.7	103.4	155.1	258.6	430.9	775.7						
50	19.5	51.7	103.4	155.1	258.6	430.9	775.7						
100	17.7	51.5	103	154.6	257.6	429.4	773						
150	15.8	50.3	100.3	150.6	250.8	418.2	752.8						
200	13.8	48.6	97.2	145.8	243.4	405.4	729.8						
250	12.1	46.3	92.7	139	231.8	386.2	694.8						
300	10.2	42.9	85.7	128.6	214.4	357.1	642.6						
325	9.3	41.4	82.6	124	206.6	344.3	619.6						
350	8.4	40.3	80.4	120.7	201.1	335.3	603.3						
375	7.4	38.9	77.6	116.5	194.1	323.2	581.8						
400	6.5	36.5	73.3	109.8	183.1	304.9	548.5						
425	5.5	35.2	70	105.1	175.1	291.6	524.7						
450	4.6	33.7	67.7	101.4	169	281.8	507						
475	3.7	31.7	63.4	95.1	158.2	263.9	474.8						
500	2.8	28.2	56.5	84.7	140.9	235	423						
538	1.4	18.4	36.9	55.3	92.2	153.7	276.6						
550	1.4(a)	15.6	31.3	46.9	78.2	130.3	234.5						
575	1.4(a)	10.5	21.1	31.6	52.6	87.7	157.9						
600	1.4(a)	6.9	13.8	20.7	34.4	57.4	103.3						
625	1.4(a)	4.5	8.9	13.4	22.3	37.2	66.9						
650	1.1(a)	2.8	5.7	8.5	14.2	23.6	42.6						

(a) Flanged-end valve ratings terminate at 538°C.

#### A 217 Gr. C5 (3) (5)

TEMP.		WORK	ING PRE	SSURE	S BY CL/	ASS, ba	r
°C	150	300	600	900	1500	2500	4500
-29 to 38	20	51.7	103.4	155.1	258.6	430.9	775.7
50	19.5	51.7	103.4	155.1	258.6	430.9	775.7
100	17.7	51.5	103	154.6	257.6	429.4	773
150	15.8	50.3	100.3	150.6	250.8	418.2	752.8
200	13.8	48.6	97.2	145.8	243.4	405.4	729.8
250	12.1	46.3	92.7	139	231.8	386.2	694.8
300	10.2	42.9	85.7	128.6	214.4	357.1	642.6
325	9.3	41.4	82.6	124	206.6	344.3	619.6
350	8.4	40.3	80.4	120.7	201.1	335.3	603.3
375	7.4	38.9	77.6	116.5	194.1	323.2	581.8
400	6.5	36.5	73.3	109.8	183.1	304.9	548.5
425	5.5	35.2	70	105.1	175.1	291.6	524.7
450	4.6	33.7	67.7	101.4	169	281.8	507
475	3.7	27.9	55.7	83.6	139.3	232.1	417.8
500	2.8	21.4	42.8	64.1	106.9	178.2	320.7
538	1.4	13.7	27.4	41.1	68.6	114.3	205.7
550	1.4(a)	12	24.1	36.1	60.2	100.4	180.7
575	1.4(a)	8.9	17.8	26.7	44.4	74	133.3
600	1.4(a)	6.2	12.5	18.7	31.2	51.9	93.5
625	1.4(a)	4	8	12	20	33.3	59.9
650	0.9(a)	2.4	4.7	7.1	11.8	19.7	35.5

(a) Flanged-end valve ratings terminate at 538°C.

#### A 217 Gr. C12 (3)(5)

TEMP.		WORKING PRESSURES BY CLASS, bar											
°C	150	300	600	900	1500	2500	4500						
-29 to 38	20	51.7	103.4	155.1	258.6	430.9	775.7						
50	19.5	51.7	103.4	155.1	258.6	430.9	775.7						
100	17.7	51.5	103	154.6	257.6	429.4	773						
150	15.8	50.3	100.3	150.6	250.8	418.2	752.8						
200	13.8	48.6	97.2	145.8	243.4	405.4	729.8						
250	12.1	46.3	92.7	139	231.8	386.2	694.8						
300	10.2	42.9	85.7	128.6	214.4	357.1	642.6						
325	9.3	41.4	82.6	124	206.6	344.3	619.6						
350	8.4	40.3	80.4	120.7	201.1	335.3	603.3						
375	7.4	38.9	77.6	116.5	194.1	323.2	581.8						
400	6.5	36.5	73.3	109.8	183.1	304.9	548.5						
425	5.5	35.2	70	105.1	175.1	291.6	524.7						
450	4.6	33.7	67.7	101.4	169	281.8	507						
475	3.7	31.7	63.4	95.1	158.2	263.9	474.8						
500	2.8	28.2	56.5	84.7	140.9	235	423						
538	1.4	17.5	35	52.5	87.5	145.8	262.4						
550	1.4(a)	15	30	45	75	125	225						
575	1.4(a)	10.5	20.9	31.4	52.3	87.1	156.8						
600	1.4(a)	7.2	14.4	21.5	35.9	59.8	107.7						
625	1.4(a)	5	9.9	14.9	24.8	41.4	74.5						
650	1.4(a)	3.5	7.1	10.6	17.7	29.5	53.2						

(a) Flanged-end valve ratings terminate at 538°C.

#### A 351 Gr. CF8M (6)

TEMP.	WORKING PRESSURES BY CLASS, bar												
°C	150	300	600	900	1500	2500	4500						
-29 to 38	19	49.6	99.3	148.9	248.2	413.7	744.6						
50	18.4	48.1	96.2	144.3	240.6	400.9	721.7						
100	16.2	42.2	84.4	126.6	211	351.6	632.9						
150	14.8	38.5	77	115.5	192.5	320.8	577.4						
200	13.7	35.7	71.3	107	178.3	297.2	534.9						
250	12.1	33.4	66.8	100.1	166.9	278.1	500.6						
300	10.2	31.6	63.2	94.9	158.1	263.5	474.3						
325	9.3	30.9	61.8	92.7	154.4	257.4	463.3						
350	8.4	30.3	60.7	91	151.6	252.7	454.9						
375	7.4	29.9	59.8	89.6	149.4	249	448.2						
400	6.5	29.4	58.9	88.3	147.2	245.3	441.6						
425	5.5	29.1	58.3	87.4	145.7	242.9	437.1						
450	4.6	28.8	57.7	86.5	144.2	240.4	432.7						
475	3.7	28.7	57.3	86	143.4	238.9	430.1						
500	2.8	28.2	56.5	84.7	140.9	235	423						
538	1.4	25.2	50	75.2	125.5	208.9	375.8						
550	1.4(a)	25	49.8	74.8	124.9	208	374.2						
575	1.4(a)	24	47.9	71.8	119.7	199.5	359.1						
600	1.4(a)	19.9	39.8	59.7	99.5	165.9	298.6						
625	1.4(a)	15.8	31.6	47.4	79.1	131.8	237.2						
650	1.4(a)	12.7	25.3	38	63.3	105.5	189.9						
675	1.4(a)	10.3	20.6	31	51.6	86	154.8						
700	1.4(a)	8.4	16.8	25.1	41.9	69.8	125.7						
725	1.4(a)	7	14	21	34.9	58.2	104.8						
750	1.4(a)	5.9	11.7	17.6	29.3	48.9	87.9						
775	1.4(a)	4.6	9	13.7	22.8	38	68.4						
800	1.2(a)	3.5	7	10.5	17.4	29.2	52.6						
816	1.0(a)	2.8	5.9	8.6	14.1	23.8	42.7						

#### (a) Flanged-end valve ratings terminate at 538°C.

A 351 Gr. CF3M (7)

TEMP.		WORKING PRESSURES BY CLASS, bar												
°C	150	300	600	900	1500	2500	4500							
-29 to 38	15.9	41.4	82.7	124.1	206.8	344.7	620.5							
50	15.3	40	80	120.1	200.1	333.5	600.3							
100	13.3	34.8	69.6	104.4	173.9	289.9	521.8							
150	12	31.4	62.8	94.2	157	261.6	470.9							
200	11.2	29.2	58.3	87.5	145.8	243	437.3							
250	10.5	27.5	54.9	82.4	137.3	228.9	412							
300	10	26.1	52.1	78.2	130.3	217.2	391							
325	9.3	25.5	51	76.4	127.4	212.3	382.2							
350	8.4	25.1	50.1	75.2	125.4	208.9	376.1							
375	7.4	24.8	49.5	74.3	123.8	206.3	371.3							
400	6.5	24.3	48.6	72.9	121.5	202.5	364.6							
425	5.5 23.9		47.7	71.6	119.3	198.8	357.9							
450	4.6	4.6 23.4 46.8 70.2			117.1	195.1	351.2							

#### General Notes:

- (1) Upon prolonged exposure to temperatures above 425°C, the carbide phase of steel may be converted to graphite. Permissible, but not recommended for prolonged use above 425°C.
- (3) Use normalized and tempered material only.
- (4) Not to be used over 595°C.
- (5) The deliberate addition of any element not listed in ASTM A 217, Table 1, is prohibited, except that Ca and Mg may be added for deoxidation.
- (6) At temperatures over 538°C, use only when the carbon content is 0.04% or higher.
- (7) Not to be used over 425°C.

<sup>(</sup>a) Flanged-end valve ratings terminate at 538°C.

### **SPECIFICATION OF CAST VALVE MATERIALS**

#### BODY AND BONNET, WEDGE–DISC–PACKING FLANGE

	DESCRIPTION	C4	RBON ST	FFI		ALLOY S	TEEL		STAINLESS STEEL						
					11/4Cr-1/2Mo	21/4Cr-1Mo	5Cr	9Cr-1Mo	13Cr		316	316L	304		
	ASTM DESIGNATION	A216 WCB	A352 LCB	A352 LCC	A217 WC6	A217 WC9	A217 C5	A217 C12	A217 CA15	A296 CA40	A351 CF8M	A351 CF3M	A351 CF8		
	Carbon	0.25(1)	0.25(1)	0.25	0.20	0.18	0.20	0.20	0.15	0.10-0.40	0.08	0.03	0.08		
8	Manganese	1.00	1.00	1.20	0.50-0.80	0.40-0.70	0.40-0.70	0.35-0.65	1.00	1.00	1.50	1.50	1.50		
Z	Phosphorus	0.04	0.04	0.04	0.04	0.40	0.04	0.04	0.04	0.04	0.04	0.04	0.04		
18	Sulphur	0.045	0.045	0.045	0.045	0.045	0.045	0.045	0.040	0.040	0.040	0.040	0.040		
S	Silicon	0.60	0.60	0.60	0.60	0.60	0.75	1.00	1.50	1.50	1.50	1.50	2.00		
12	Nickel	0.50	_	0.50	0.50	0.50	0.50	0.50	1.00	1.00	9.00-12.00	9.00-13.00	8.00-11.00		
COMPOSITION	Chromium	0.50		0.50	1.00-1.50	2.00-2.75	4.00-6.50	8.00-10.00	11.5-14.0	11.5-14.0	18.00-21.00	17.00-21.00	18.00-21.00		
10	Molybdenum	0.20		0.20	0.45-0.65	0.90-1.20	0.45-0.65	0.90-1.20	0.50	0.50	2.0-3.00	2.0-3.00	0.50		
	Copper	0.30	0.30	0.30	0.50		0.50	0.50	—	_		—	—		
	Heat treatment	Anneal	Quench a	nd temper		Tempe	er		Solution anneal						
	Tensile psi min.	70,000	65,000- 90,000	70,000- 95,000	70,000	-90,000	90,000	-115,000	90,000- 115,000	100,000	70,000	70,000	70,000		
	Yield psi min.	36,000	35,000	40,000	40,000	40,000	60,000	60,000	65,000	70,000	30,000	30,000	30,000		
E	Elongation % min.	22	24	22	20	20	18	18	18	15	30	30	35		
	Reduction of area % min.	35	35	35	35	35	35	35	30	25	—	—	—		
	Hardness HB	187 max.	197 max.	200 max.	207 max.	207 max.	241 max.	241 max.	327-381	475 min.	_	187 max.	_		
	Parts			BODIES	–BONNETS–L	ARGE DISCS			DISC MA	TERIALS	BODIES	S-BONNETS	-DISCS		

(1) Velan standard: 0.25 or less.

#### TRIM SPECIFICATION

					BAR ST	ОСК					CAST	
וח	ASTM ESIGNATION	13	Cr	St	tainless steels	5	М	onel	Hastelloy	Monel	CoCr alloy	Austenitic ductile
	ESIGNATION	A479 410*	A582 416*	A 479 316 St. Hard.	A479 316	A564 630	B164 Monel	AMS 4676D K-Monel	B574 N 10276	A494 M-25S	AMS 5387 A	A439 D-2C
	Carbon	0.15	0.15	0.08	0.08	0.07	0.3	0.25	0.010	0.25	0.9–1.4	2.90
	Manganese	1.00	1.25	2.00	2.00	1.00	2.0	1.50	1.0	1.50	1.0	1.80-2.40
	Phosphorus	0.040	0.06	0.045	0.045	0.040	-	0.02	0.04	0.03	0.04	0.08
%	Sulphur	0.030	0.15 min.	0.030	0.030	0.030	0.024	0.010	0.03	0.03	0.04	-
	Silicon	1.00	1.00	1.00	1.00	1.00	0.5	1.00	0.08	3.5–4.5	1.5	1.00–3.00
8	Nickel	-	_	10.00-14.00	10.00-14.00	3.00-5.00	63.0	63.00-70.00	Balance	Balance	3.0	1.00-24.00
.IS	Chromium	11.50-13.50	12.00-14.00	16.00-18.00	16.00-18.00	15.00-17.50	-	-	14.5-16.5	-	27.0-31.0	0.50
PO	Molybdenum	-	-	2.00-3.00	2.00-3.00	-	-	-	15.0-17.0	-	1.5	-
COMPOSITION	Copper	-	-	-	-	3.00-5.00	28.0-34.0	Balance	-	27.0-33.0	-	-
5	Aluminum	-	-	-	-	-	3.00	-	3.00	-	-	-
	Cobalt	-	-	-	-	-	-	-	-	-	Balance	-
	Tungsten	-	_	-	-	-	-	-	-	-	3.5-5.5	-
	Iron	-	_	-	-	-	-	-	-	3.50	3.0	-
Spe	ecial condition	Temper	Hard	Level 2	-	_	Hot worked	Hot finished	-	Age hardened	-	-
He	eat treatment	Class 2	Hard temper	Solution annealed	Solution annealed	H 1100	-	-	-	-	-	-
Te	ensile psi min.	110,000	-	95,000	75,000	140,000	80,000	140,000	100,000	-	130,000	58,000
Y	'ield psi min.	85,000	_	75,000	30,000	115,000	40,000	100,000	41,000	-	-	28,000
Eloi	ngation % min.	15	-	25	30	14	30	20	40	-	1	20
Rec	uction of area % min.	45	_	40	40	45	-	-	-	-	-	-
H	lardness HB	269 max.	293–352	-	-	302 min.	-	326 min.	-	300 min.	344 min.	121–171


\* 13Cr or Monel trim also available in soft form (less than 237 HB). Non-cobalt hardfacing also available.

#### **SOUR SERVICE VALVES**

Where NACE or sour service is specified, valves comply with NACE MR0103 or MR0175 / ISO15156. It is the end user's responsibility to install the valves in the service conditions permitted by these standards.

### For trim material (wedge/disc surface, seat surface, and stem) see page 27.

TRIM	
NA, ND, NE, NF:	B7M / 2HM Rc. 22 Max.
NB, NC, NN:	B7M / 2HM, B8M / 8 or Rc. 22 Max.



The figure numbers shown on this key are designed to cover essential features of Velan valves. Please use figure numbers to ensure prompt and accurate processing of your order. A detailed description must accompany any special orders.

Α	TYP	ΕO	F C	10	١N	IEC1	ΓΙΟ	)V	1							
Α	Special		D	DIN	l Fla	inged					F			nged E 1 605)	316.47	series B
В	Butt we	Butt weld <b>E</b> Welded studs (butt wel								d)	F	-		nged r	ing jo	int
C	Combin	Combination <b>F</b> Flanged B16.5 (B16.47 series									ί	ו	Und	drilled	flang	es
B	SIZE	: 0	FC		N	FCT		N			_					
( <b>B</b> ) Size	tomers have the choice of specifying valve size as part of the valve figure number using the numbers below, or indicating valve size separately. as shown in NPS (DN)															
F10	EXAMPLES: E10-0064C-02TY (valve size is part of figure number) 8 (80) F-0064C-02TY (valve size is shown separately)															
08	2 (50)	14	6 (15	50)	21	18 (45	50)	30	3	80 (750)	4	2	42 (	1050)	56	56 (1400)
09	21⁄2 (65)	15	8 (20	)0)	22	20 (50	)0)	32	3	32 (800)	4	4	44 (	1100)	60	60 (1500)
10	3 (80)	16	10 (2	250)	23	22 (55	50)	34	3	84 (850)	4	6	46 (	1150)	64	64 (1600)
11	3½ (90)	18	12 (3	300)	24	24 (60	)0)	36	3	36 (900)	4	8	48 (	1200)	99	Special
12	4 (100)	19	14 (3		26	26 (65		38		38 (950)	5	-		1250)		
13	5 (125)	20	16 (4	100)	28	28 (70	)0)	40	4	0 (1000)	54	4 !	54 (	1350)		
С	PRE	SS	UR	RE F	<b>A</b>	TIN	G									
0	150	1	300		2	600		3	1	500 <b>7</b>	'	900	)	X	Butt	weld
D	VAI		E T	/PE												
01	Flow c	ontro	1	07	S	top glo	he	Т	09	Needle	,	_	Т	99	Secia	al
06	Full po			08	-	top che			11	Swing	ch	eck				
Е	BO	DY/	'BC	N	JE.	T S	ΓY	LE		1						
4	Vertica	ıl	_	_			П	Α	S	pecial				_	_	
	1						-1	C	В	olted bo	nne	et (d	ast	t)		
							ĺ	Ε	E	xtended	boı	nne	t (c	ryoge	nic)	
								V	С	ast bolte	d b	oni	net	bellov	vs se	al
F	BOI	DY	MA	TE	RI		)									
01	Specia	I	09	C1	2		1	9	M	onel M35	1	3	1	LCC		
02	WCB		11	CF	8		2	3	All	oy 20		3	4	C12/	A (F91	)
		_	12	CF	3		2	5	LC	В		3	8	LC1	_	
03	WC1		12		-		_	-	_		_	÷ –				
04	C5		13	CF	8M		2		LC	-			9	LC2		
				CF	8M 3M		2	8	CG	3 88M 83M			19 16	LC2 GS-0	25N	

(1) Pressure-containing valve components which may include body, bonnet, cover and body end.

**Note:** CoCr alloy as used throughout this catalog refers to cobalt chrome hardfacing alloys as supplied by Kennametal Stellite<sup>™</sup>, and other approved manufacturers.

For a more detailed list of available trims, contact the factory or visit our web site at www.velan.com.

G	Т	RIM (standard trin	ns)			
Code		Wedge/disc surface <sup>(2)</sup>	Seat surface <sup>(2)</sup>	Stem	API Number	Bellows <sup>(3)</sup> (if applicable)
MS	ъ	CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	316	16	321
MY	ladr	CF8M or 316	CoCr alloy <sup>(4)</sup>	316	12	321
TS	Standadrd	CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	13 Cr (410) <sup>(5)</sup>	5	321
ТҮ	S	13 Cr (410 or CA15)	CoCr alloy <sup>(4)</sup>	13 Cr (410)	8	
NA	13 Cr (410 or CA15) HRC 22 max.		CoCr alloy <sup>(4)</sup>	13 Cr 410 HRC 22 max.	8	
NB	1	CF8M	CoCr alloy <sup>(4)</sup>	316	12	321
NC		Monel	CoCr alloy <sup>(4)</sup>	Monel	11	Hastelloy C
ND	ce <sup>(7</sup>	CoCr alloy <sup>(3</sup>	CoCr alloy <sup>(3</sup>	630 (H1150M)	5(8)	
NE	NACE service <sup>(7)</sup>	CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	13 Cr 410 HRC 22 max.	5	
NF	ACE	CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	Same as body		
NG	ź	CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	316	16	
NN		CF8M	CoCr alloy <sup>(4)</sup>	316	12	
NX		Monel	Monel	Monel	9	
NY		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	XM-19	16 <sup>(9)</sup>	
AS		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	321	16 <sup>(10)</sup>	321
AY		CF8C/F321	CoCr alloy <sup>(4)</sup>	321	12 <sup>(10)</sup>	321
CC		Alloy 20	Alloy 20	Alloy 20	13	
ES		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	347	16 <sup>(10)</sup>	
EY		CF8C/F347	CoCr alloy <sup>(4)</sup>	347	12 <sup>(10)</sup>	
HC		Hastelloy C	CoCr alloy <sup>(4)</sup>	Hastelloy C		Hastelloy C
НМ		HF-acid trim	HF-acid trim	HF-acid trim		
MF	CF	8M or 316 w/ Teflon insert <sup>(6)</sup>	CoCr alloy <sup>(4)</sup>	316	12	
MH		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	316	16	Hastelloy C
MN		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	316	16	Inconel 625
МХ		CF8M	316	316	10	
TF		13Cr (410 or CA15) w/ Teflon insert <sup>(6)</sup>	CoCr alloy <sup>(4)</sup>	13 Cr (410)	8	
TH		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	13 Cr (410) <sup>(5)</sup>	5	Hastelloy C
ΤN		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	13 Cr (410) <sup>(5)</sup>	5	Inconel 625
XS		CoCr alloy <sup>(4)</sup>	CoCr alloy <sup>(4)</sup>	Monel		
ХХ		Monel	Monel	Monel	9	
ХҮ		Monel	CoCr alloy <sup>(4)</sup>	Monel	11	

(2) Base material is either the same as the body or solid trim at manufacturer's option.

(3) Bellows material shown as standard, Inconel can be used in lieu of 321 and Hastelloy C in lieu of Inconel, where design and/or pressure class applicable.

(4) CoCr alloy refers to cobalt-chrome alloys in Grade 6 (e.g. AWS CoCr-A, UNS 30006 & 30106) or Grade 21 (e.g. AWS CoCr-E, UNS 30021). Use of Grade 6 or 21 is at Velan's option.

(5) 616HT manufacturer's standard. (F91 and C12A only).

(6) Inserts may be in seat or wedge at manufacturer's option.

(7) Valves with "NACE" figure numbers will meet the material requirements of NACE MR0103 and MR0175/ISO 15156. It is the equipment user's responsibility to ensure that the materials are suitable for the intended service.

(8) 630 SS is a Precipitation - Hardenable Stainless Steel (Also referred to as 17-4 PH stainless steel) Has superior Mechanical properties and adequate corrosion resistance when compared to 410 SS.

(9) XM-19 is an austenitic stainless steel known for its superior mechanical properties and corrosion resistance compared to 316 SS.

(10) An austenitic stainless steel which has comparable mechanical properties and corrosion resistance compared to 316. The most comprehensive line of industrial forged and cast steel gate, globe, check, ball, butterfly, and knife gate valves and steam traps.

ASME pressure classes 150–4500 in carbon, alloy, and stainless steel



**WARNING:** The use of chainwheels may present a risk of serious injury to personnel or damage to property if the chainwheel becomes detached and falls. The end user and purchaser shall be responsible to ensure the correct installation, operation, maintenance and safety provisions related to chainwheels. Velan does not assume any liability whatsoever for the safe application and operation of chainwheels supplied by parties other than Velan or for chainwheels that are used without a suitably designed safety device.

© 2019 Velan Inc., Montreal, QC, Canada. All rights reserved. The contents hereof are confidential and proprietary to Velan. Any unauthorized reproduction or disclosure, in whole or in part, is strictly prohibited. The material in this catalog is for general information only and shall not be used for specific performance data and material selection without first consulting Velan. Velan reserves the right to change this information without notice. Velan does not accept any liability or damages arising from the use of information in this catalog. Velan, Velan Ultraflex, Steamless, Moss, Torqseal, Memoryseal, Securaseal, Velflex, Rama, Clama, Adareg, and Rama Clama II are trademarks or registered trademarks of Velan Inc. and/or another Velan company. One or more of these trademarks are registered in certain countries/regions, please contact Velan Inc.'s legal department for further information. All other trademarks and registered trademarks are owned by their respective companies.



Headquartered in Montreal, Canada, Velan has several international subsidiaries. For general inquiries:

#### Velan head office

7007 Côte de Liesse, Montreal, QC H4T 1G2 Canada **Tel:** +1 514 748 7743 **Fax:** +1 514 748 8635

Check our website for more specific contact information.

#### www.velan.com

CAT-CSV-09-18a

Printed in Canada